3MTM Dri-Shield Moisture Barrier Bag 3000

Moisture Barrier Bag ~ Foil

3M's Dri-Shield 3000 Moisture Barrier Bag is designed to meet the requirements of IPC/JEDEC J-STD-033 for the dry packaging of electronic devices. Dri-Shield 3000 bags are made from dissipative nylon, foil, and dissipative polyethylene. These bags protect SMD's from moisture and static damage. Flexible structure is easy to vacuum seal. Coded for QC traceability.

Standards

Meets electrical and physical requirements of IPC/JEDEC J-STD-033, MIL-PRF-81705 Type 1, EIA 583, EIA 541, EIA 625, and EOS/ESD Standards.

Specifications

Physical Properties: Typical Values

MVTR(g/100 sq.in./24 hrs) <.0003 ASTM F 1249
Puncture Resistance 17 lbs FTMS 101 MTH 2065

Thickness 6.1 mils 3M 008
Tensile Strength >4500 psi ASTM D882
Seam Strength Pass MIL-PRF-81705

Heat Sealing Conditions:

 Temperature
 300°F - 400°F

 Time
 0.6 - 4.5 seconds

 Pressure
 30 - 70 PSI

Electrical Properties:

Surface Resistivity / Resistance ASTM D257 or ANSI/ESD STM11.11 Interior <10¹² ohms/square or <10¹¹ ohms Exterior <10¹² ohms/square or <10¹¹ ohms

Metal 100 ohms

Static Shielding < 15 volts EIA 541

Static Shielding< 10 nJ</th>EOS/ESD S11.31EMI Attenuation45 dBMIL-PRF-81705Static Decay< 0.03 seconds</td>FTMS 101 MTH 4046Non-CorrosivePassFTMS 101 MTH 3005

Outgassing Pass ASTM E595



3M™ Dri-Shield 3000 Bag







Material Structure

6.1 mils of static dissipative nylon, aluminum foil, and static dissipative polyethylene provide a very low MVTR. This foil barrier material meets or exceeds the MVTR and EMI/RFI/Static Shielding requirements of IPC/JEDEC J-STD-033

MIL-PRF-81705 Type I, and EIA 583, for static safe, moisture barrier packaging





See 3M Data Sheets for these related items:

Humidity Indicator Cards (HIC's)

Desiccant 113 Label

Vacuum Sealers

PRODUCT DATA SHEET

Dri-Shield 3000 Moisture Barrier Bag FOIL

PRODUCT
MOISTURE BARRIER BAG, FOIL

ITEM NUMBER D30(W")(L")

DATASHEET 1104-B

3M Electronic Solutions Division 6801 River Place Blvd. Austin TX 78726-9000

Austin, TX 78726-9000 US and Canada: **866-722-3736**

Fax: 866-722-3735

Intl: 919-718-0000; Fax: 919-774-8174

email: 3Mstaticinfo@mmm.com; www.3M.com/static

3M is a trademark of 3M Company.

All other trademarks herein are the property of their respective owners.



3MTM Dri-Shield Moisture Barrier Bag 3000

Moisture Barrier Bag ~ Foil

W"x L" P/N

10 x 20 D301020


10 x 30 D301030

16 x 18 D301618

• All standard sizes in-stock/same day shipment.

- Width is measured from inside seam to inside seam.
- Length is measured from the top edge to the bottom fold.
- Opening is in the "width" dimension.
- Custom bag sizes, custom printing, and custom hot stamping are available.
- Most sizes are packed 100 per case. Small sizes are packed 1000 or 500 per case.

3MTM Dri-Shield 3000 Bag



How Moisture Barrier Bags Work

Moisture barrier bags work by enclosing a device with a metal or plastic shield(s) that have a high resistance to moisture vapor permeation. Dry devices are placed inside this shield, and the moisture-laden air is evacuated. Desiccant filled pouches scavenge the remaining moisture from the bag's interior. Moisture that penetrates the bag is also entrapped by the desiccant. Humidity indicating cards report the effectiveness of the package upon device use. A label on the bag indicates the amount of exposure time devices are allowed prior to use, and the drying (re-baking) time and temperature if the exposure time is exceeded.

As the barrier property improves, the Moisture Vapor Transmission Rate (MVTR) decreases. Bags with lower MVTR provide better barrier. Aluminum foil provides the best MVTR of about 0.0003. Multiple layers of Foil Polyester can provide 0.02 to about 0.005.

Puncture Resistance is an important feature for barrier bags. Sharp tray edges may tear through bags with low puncture resistance.

т

E E

О **Dri-Shield 3000** Static Shielding Bag METAL-IN

R

PRODUCT

MOISTURE BARRIER BAG, FOIL

ITEM NUMBER D30(W")(L")

СТ

D U

DATASHEET

D

A T A

1104-B

3M Electronic Solutions Division 6801 River Place Blvd. Austin, TX 78726-9000

US and Canada: 866-722-3736

Fax: 866-722-3735

Intl: 919-718-0000: Fax: 919-774-8174

email: 3Mstaticinfo@mmm.com: www.3M.com/static

S H

3M is a trademark of 3M Company.

@ 2008

All other trademarks herein are the property of their respective owners.

