
DATA SHEET

Product Number: 310-43-105-41-105000



Description:

Interconnect Socket .100 Grid; Surface Mount Socket Single Row Gull Wing; Left Hand Footprint Single Row Surface Mount Accepts .015-.025" Leads Plating Code:

43

#30 CONTACT

OPERATING RANGE

0.020

MATING PIN DIAMETER (inches)

0.018

Shell Plating:

200 $\mu^{\text{\tiny{"}}}$ Tin (matte finish) over 100 $\mu^{\text{\tiny{"}}}$ Nickel

Inner Contact Plating: 30 μ" Gold over 50 μ" Nickel

#	Mill-Max	RoHS
Of	Part	Compliant
Pins	Number	

1000

FORCE (grams)

100

5 310-43-105-41-105000



INITIAL INSERTION FORCE

0.023

INSERTION FORCE 2nd CYCLE
EXTRACTION FORCE

0.024

0.026

CONTACT:

Contact Used: #30, Standard 4 Finger Contact

Current Rating = 3 Amps

BERYLLIUM COPPER ALLOY 172 (UNS C17200) per ASTM B 194

Properties of BERYLLIUM COPPER:

• Chemical composition: Cu 98.1%, Be 1.9%

Temper as stamped: TD01

Properties after heat treatment (TH01):

• Hardness: 36-43 Rockwell C

• Mechanical Life: 100 Cycles Min.

• Density: .298 lbs/in3

Electrical Conductivity: 22% IACS*

• Resistance: 10 miliohms Max

• Operating Temperature: -55°C/+125°C



10

0.01

0.012 0.013 0.015

^{*}International Annealed Copper Standard, i.e. as a % of pure copper.

[†]Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

LOOSE PIN:

Loose Pin Used: 1005

BRASS ALLOY (UNS C36000) per ASTM B 16

Properties of BRASS ALLOY:

• Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†

• Hardness as machined: 80-90 Rockwell B

• Density: .307 lbs/in3

Electrical conductivity: 26% IACS*

• Melting point: 900°C/885°C (liquidus/solidus)

†(3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

*International Annealed Copper Standard, i.e. as a % of pure copper.

INSULATOR INFORMATION:

PCT Polyester, (Thermx CG933, black)

High Temperature

Properties of PCT Polyester:

Brand: ThermxGrade: CG-933

• Rated voltage: 100 VRMS/150 VDC

• Insulation resistance: 10,000 Megaohms min.

• Material Heat Deflection Temp (per ASTM D 648): 529°F (276°C) @ 66 psi

• Dielectric strength: 1000 VRMS min. (700 VRMS min. for series 117 Shrink DIP)

Note: Materials above 446°F (230°C) are considered suitable for "eutectic" reflow soldering, above 500°F (260°C) for "lead-free" reflow soldering.