
# **DATA SHEET**

Product Number: 415-43-210-41-001000



#### **Description:**

Interconnect Socket .100 Grid; Low Profile Socket Very Low Profile Double Row Through Hole Accepts .015-.025" Leads

## **Plating Code:**

43

#### Shell Plating:

200  $\mu^{\text{"}}$  Tin (matte finish) over 100  $\mu^{\text{"}}$  Nickel

#### **Inner Contact Plating:**

30  $\mu$ " Gold over 50  $\mu$ " Nickel

# Of Pins	Mill-Max Part Number	RoHS Compliant
10	415-43-210-41-001000	RoHS 2002/96/EQ

#### **CONTACT:**

Contact Used: #30, Standard 4 Finger Contact

Current Rating = 3 Amps

**BERYLLIUM COPPER ALLOY** 172 (UNS C17200) per ASTM B 194

## **Properties of BERYLLIUM COPPER:**

• Chemical composition: Cu 98.1%, Be 1.9%

• Temper as stamped: TD01

Properties after heat treatment (TH01):

• Hardness: 36-43 Rockwell C

Mechanical Life: 100 Cycles Min.

Density: .298 lbs/in3

Electrical Conductivity: 22% IACS\*

Resistance: 10 miliohms Max

• Operating Temperature: -55°C/+125°C

• Melting point: 980°C/865°C (liquidus/solidus)

 $\bullet$  Stress Relaxation†: 96% of stress remains after 1,000 hours @ 100 °C ; 70% of stress remains after 1,000 hours @ 200 °C



†Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

<sup>\*</sup>International Annealed Copper Standard, i.e. as a % of pure copper.

#### **LOOSE PIN:**

Loose Pin Used: 0501

BRASS ALLOY (UNS C36000) per ASTM B 16

### **Properties of BRASS ALLOY:**

• Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†

• Hardness as machined: 80-90 Rockwell B

• Density: .307 lbs/in3

• Electrical conductivity: 26% IACS\*

• Melting point: 900°C/885°C (liquidus/solidus)

†(3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

#### **INSULATOR INFORMATION:**

PBT\* Polyester, (Valox 420-SEO, black), Self-extinguishing, rated UL94V-0

Standard Temperature

## **Properties of PBT Polyester:**

Brand: ValoxGrade: 420-SEOColor: Black

• Rated voltage: 100 VRMS/150 VDC

• Insulation resistance: 10,000 Megaohms min.

• Dielectric strength: 1000 VRMS min. (700 VRMS min. for series 117 Shrink DIP)

• Material Heat Deflection Temp (per ASTM D 648): 420°F(216°C) @ 66 psi

• Resistant to detergents, mineral acids, solvents, greases and oils (short time)

<sup>\*</sup>International Annealed Copper Standard, i.e. as a % of pure copper.