

Data Sheet

Customer:

Product: Multilayer Ceramic Chip Capacitor – MC Series

Sizes.: 0201/0402/0603/0805/1206/1210/1808/1812/0612

Issued Date: 08-Aug-19

Edition: REV.B4



VIKING TECH CORPORATION
光頤科技股份有限公司
No.70, Guangfu N. Rd., Hukou
Township, Hsinchu County
303, Taiwan (R.O.C)

TEL:886-3-5972931
FAX:886-3-5972935•886-3-5973494
E-mail:sales@viking.com.tw

VIKING TECH CORPORATION KAOHSIUNG BRANCH
光頤科技股份有限公司高雄分公司
No.248-3, Sin-Sheng Rd., Cian-Jhen Dist., Kaohsiung,
806, Taiwan

TEL:886-7-8217999
FAX:886-7-8228229
E-mail:sales@viking.com.tw

VIKING ELECTRONICS (WUXI) CO., LTD.
光頤電子(無錫)有限公司
No.22 Xixia Road, Machinery & Industry Park,
National Hi-Tech Industrial Development Zone
of Wuxi, Wuxi, Jiangsu Province, China
Zip Code:214028
TEL:86-510-85203339
FAX:86-510-85203667•86-510-85203977
E-mail:china@viking.com.tw


Produced by (QC)	Checked (QC)	Approved by (QC)	Prepared by (Sales)	Accepted by (Customer)
08-Jul-19	08-Jul-19	08-Jul-19	08-Jul-19	
Kris Chen	Ben Chang	Ben Chang		

Multilayer Ceramic Chip Capacitor



Features

- Wide capacitance range, extremely compact size
- Low inductance of capacitor for high frequency application
- Excellent solderability and resistance to soldering heat, suitable for flow and reflow soldering
- Adaptable to high-speed surface mount assembly
- Conform to EIAJ-RC3402, and also compatible with EIA-RS198 and IEC PUB. 384-10

Construction



①	Ceramic Material	③	Termination:
②	Inner Electrodes		NPO: Ag/Ni/Sn dielectric X7R, Y5V, X5R: Cu/Ni/Sn dielectric



Unit: mm

Dimensions

MC / MCRF Type

Type	Size (Inch)	L	W	T / Symbol		M _B	Packaging (7" Reel)	
							Paper tape	Plastic tape
01	0201	0.6±0.03	0.3±0.03	0.3±0.03	L	0.15±0.05	15K	-
		0.6±0.05 ^{#2}	0.3±0.05 ^{#2}	0.3±0.05 ^{#2}				
		0.6±0.09 ^{#3}	0.3±0.09 ^{#3}	0.3±0.09 ^{#3}				
02	0402	1.00±0.05	0.50±0.05	0.50±0.05	N	0.25 +0.05 / -0.10	10K	-
				0.50±0.02/-0.05	Q			
		1.00±0.20	0.50±0.20	0.50±0.20	E			
03	0603	1.60±0.10	0.80±0.10	0.80±0.10	S	0.40±0.15	4K	-
		1.60+0.15/-0.10	0.80+0.15/-0.10	0.50±0.10	H			
				0.80+0.15 / -0.10	X			
		1.60±0.20 ^{#1}	0.80±0.20 ^{#1}	0.80±0.20 ^{#1}				
05	0805	2.00±0.15	1.25±0.10	0.50±0.10	H	0.50±0.20	4K	-
				0.60±0.15	A			-
				0.80±0.10	B			-
				1.25±0.10	D			-
		2.00±0.20	1.25±0.20	0.85±0.10	T		-	3K
				1.25±0.20	I		4K	-
06	1206	3.20±0.15	1.60±0.15	0.80±0.10	B	0.60±0.20 (0.50±0.25) ^{***}	4K	-
				0.95±0.10	C		-	3K
				1.25±0.10	D		-	3K
				1.15±0.15	J		-	3K
		3.20±0.20	1.60±0.20	1.60±0.20	G		-	2K
				0.85±0.10	T		4K	-
		3.20+0.3 / -0.1	1.60+0.3 / -0.1	1.60+0.3 / -0.1	P		-	2K
							-	
10	1210	3.20±0.30	2.50±0.20	0.95±0.10	C	0.75±0.25	-	3K
				0.85±0.10	T		-	3K
				1.25±0.10	D		-	3K
		3.20±0.40	2.50±0.30	1.60±0.20	G		-	2K
				2.00±0.20	K		-	1K
				2.50±0.30	M		-	1K 0.5K
08	1808	4.50±0.40 (4.5+0.5/-0.3) ^{**}	2.03±0.25	1.25±0.10	D	0.75±0.25 (0.50±0.25) ^{***}	-	2K
				1.40±0.15	F		-	2K
				1.60±0.20	G		-	2K
				2.00±0.20	K		-	1K

Type	Size (Inch)	L	W	T / Symbol		M _B	Packaging (7" Reel)	
							Paper tape	Plastic tape
12	1812	4.50±0.40 (4.5+0.5/-0.3)**	3.20±0.30	1.25±0.10	D	0.75±0.25 (0.50±0.25)***	-	1K
				1.60±0.20	G		-	1K
				2.00±0.20	K		-	1K
			3.20±0.40	2.50±0.30	M		-	0.5K
				2.80±0.30	U		-	0.5K

** For 1808/1812: 200~3KV, ***For 1206:1KV~3KV; 1808/1812: 200~3KV

#1: For 0603 Cap ≥ 10uF or 0603 Cap ≥ 4.7uF (≤ 6.3V) or 0603 Cap > 1uF (> 10V) products ;

#2: For 0201/Cap ≥ 0.68uF products ;

#3: For 0201/Cap ≥ 1uF products

Low Inductance Capacitors for MCLI Type

Unit: mm

Type	Size (Inch)	L	W	T / Symbol		Ta min.	Tb min.	Packaging (7" Reel)	
								Paper tape	Plastic tape
MCLI43	0612	3.20±0.15	1.60±0.15	0.80±0.10	B	0.5	0.13	4K	-

Part Numbering

MC	03	J	T	N	250	3R9
Product Type	Dimensions (L×W)	Capacitance Tolerance	Packaging	Dielectric	Voltage (VDCW)	Capacitance
MC : General; Ultra-small Middle and High Voltage MCRF: Ultra High Q and Low ESR (RF) MCLI: Low Inductance	01: 0201 02: 0402 03: 0603 05: 0805 06: 1206 10: 1210 08: 1808 12: 1812 43: 0612	B: ±0.1pF (Cap ≤ 5pF) C: ±0.25pF (Cap ≤ 5pF) D: ±0.5pF (5pF < Cap < 10pF) F: ±1% G: ±2% J: ±5% K: ±10% M: ±20% Z: +80/-20%	T: Taping Reel	N: NPO (COG) B: X7R F: Y5V X: X5R	6V3: 6.3V 250: 25V 500: 50V 101: 100V 102: 1000V 202: 2000V 302: 3000V	3R9: 3.9pF 150: 15pF 181: 180pF 225: 2.2μF 476: 47μF 107: 100μF

■ General Capacitance & Voltage

Capacitance & Voltage (NPO)

Dielectric		NPO														
EIA	Size	0402					0603					0805				
Code	VDCW	10V	16V	25V	50V	100V	10V	16V	25V	50V	100V	10V	16V	25V	50V	100V
0R1	0.1pF	N	N	N	N											
0R2	0.2	N	N	N	N											
0R3	0.3	N	N	N	N		S	S	S	S						
0R4	0.4	N	N	N	N		S	S	S	S						
0R5	0.5	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0R6	0.6	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0R7	0.7	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0R8	0.8	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0R9	0.9	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1R0	1.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1R2	1.2	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1R5	1.5	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1R8	1.8	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
2R0	2.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
2R2	2.2	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
2R7	2.7	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
3R0	3.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
3R3	3.3	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
3R9	3.9	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
4R0	4.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
4R7	4.7	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
5R0	5.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
5R1	5.1				N											
5R6	5.6	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
6R0	6.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
6R8	6.8	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
7R0	7.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
8R0	8.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
8R2	8.2	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
9R0	9.0	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
100	10pF	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
120	12	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
150	15	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
180	18	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
220	22	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
270	27	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
330	33	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
390	39	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
470	47	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
560	56	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
680	68	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
820	82	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
101	100pF	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
121	120	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
151	150	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
181	180	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
221	220	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
271	270	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
331	330	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
391	390	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
471	470	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
561	560	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
681	680	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
821	820	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
102	1000pF	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
122	1200						X	X	X	X	X*	B	B	B	B	B
152	1500						X	X	X	X	X*	B	B	B	B	B
182	1800						X	X	X	X		B	B	B	B	B
222	2200						X	X	X	X		B	B	B	B	B
272	2700						X	X	X	X		D	D	D	D	D
332	3300						X	X	X	X		D	D	D	D	D
392	3900						X*	X*	X*	X*		D	D	D	D	D
472	4700						X*	X*	X*	X*		D	D	D	D	D
562	5600						X*	X*	X*	X*		D	D	D	D	D
682	6800						X*	X*	X*	X*		D	D	D	D	D
822	8200						X*	X*	X*	X*		D	D	D	D	D
103	0.01uF						X*	X*	X*	X*		D	D	D	D	
123	0.012											T*	T*	T*	T*	
153	0.015											T*	T*	T*	T*	
183	0.018											D*	D*	D*	D*	
223	0.022											D*	D*	D*	D*	

■ The letter in cell is expressed the symbol of product thickness

■ The letter in cell with "*" mark is expressed capacitance tolerance "J"(±5%) only

Capacitance & Voltage (NPO)

Dielectric		NPO													
EIA	Size	1206					1210					1812			
Code	VDCW	10V	16V	25V	50V	100V	10V	16V	25V	50V	100V	16V	25V	50V	100V
1R2	1.2 pF	B	B	B	B	B									
1R5	1.5	B	B	B	B	B									
1R8	1.8	B	B	B	B	B									
2R2	2.2	B	B	B	B	B									
2R7	2.7	B	B	B	B	B									
3R3	3.3	B	B	B	B	B									
3R9	3.9	B	B	B	B	B									
4R7	4.7	B	B	B	B	B									
5R6	5.6	B	B	B	B	B									
6R8	6.8	B	B	B	B	B									
8R2	8.2	B	B	B	B	B									
100	10pF	B	B	B	B	B	C	C	C	C	C	D	D	D	D
120	12	B	B	B	B	B	C	C	C	C	C	D	D	D	D
150	15	B	B	B	B	B	C	C	C	C	C	D	D	D	D
180	18	B	B	B	B	B	C	C	C	C	C	D	D	D	D
220	22	B	B	B	B	B	C	C	C	C	C	D	D	D	D
270	27	B	B	B	B	B	C	C	C	C	C	D	D	D	D
330	33	B	B	B	B	B	C	C	C	C	C	D	D	D	D
390	39	B	B	B	B	B	C	C	C	C	C	D	D	D	D
470	47	B	B	B	B	B	C	C	C	C	C	D	D	D	D
560	56	B	B	B	B	B	C	C	C	C	C	D	D	D	D
680	68	B	B	B	B	B	C	C	C	C	C	D	D	D	D
820	82	B	B	B	B	B	C	C	C	C	C	D	D	D	D
101	100pF	B	B	B	B	B	C	C	C	C	C	D	D	D	D
121	120	B	B	B	B	B	C	C	C	C	C	D	D	D	D
151	150	B	B	B	B	B	C	C	C	C	C	D	D	D	D
181	180	B	B	B	B	B	C	C	C	C	C	D	D	D	D
221	220	B	B	B	B	B	C	C	C	C	C	D	D	D	D
271	270	B	B	B	B	B	C	C	C	C	C	D	D	D	D
331	330	B	B	B	B	B	C	C	C	C	C	D	D	D	D
391	390	B	B	B	B	B	C	C	C	C	C	D	D	D	D
471	470	B	B	B	B	B	C	C	C	C	C	D	D	D	D
561	560	B	B	B	B	B	C	C	C	C	C	D	D	D	D
681	680	B	B	B	B	B	C	C	C	C	C	D	D	D	D
821	820	B	B	B	B	B	C	C	C	C	C	D	D	D	D
102	1000pF	B	B	B	B	B	C	C	C	C	C	D	D	D	D
122	1200	B	B	B	B	B	C	C	C	C	C	D	D	D	D
152	1500	B	B	B	B	B	C	C	C	C	C	D	D	D	D
182	1800	B	B	B	B	B	C	C	C	C	C	D	D	D	D
222	2200	B	B	B	B	B	C	C	C	C	C	D	D	D	D
272	2700	B	B	B	B	B	C	C	C	C	C	D	D	D	D
332	3300	B	B	B	B	B	C	C	C	C	C	D	D	D	D
392	3900	B	B	B	B	B	C	C	C	C	C	D	D	D	D
472	4700	B	B	B	B	B	C	C	C	C	C	D	D	D	D
562	5600	B	B	B	B	B	C	C	C	C	C	D	D	D	D
682	6800	C	C	C	C	C	C	C	C	C	C	D	D	D	D
822	8200	D	D	D	D	D	C	C	C	C	C	D	D	D	D
103	0.01uF	D	D	D	D	D	C	C	C	C	C	D	D	D	D
123	0.012	P	P	P	P	P	D	D	D	D	D	D	D	D	D
153	0.015	P	P	P	P	P	D	D	D	D	D	D	D	D	D
183	0.018	P	P	P	P	P	K	K	K	K	K	D	D	D	D
223	0.022	P	P	P	P	P	K	K	K	K	K	D	D	D	D
273	0.027	P	P	P	P		K	K	K	K	K	D	D	D	D
333	0.033	P	P	P	P		K	K	K	K	K	D	D	D	D
393	0.039	P	P	P	P							M	M	M	M
473	0.047	J*	J*	J*	J*							M	M	M	M
563	0.056	J*	J*	J*	J*							M	M	M	M
683	0.068	G*	G*	G*	G*							M	M	M	M
823	0.082	G*	G*	G*	G*							M	M	M	M
104	0.10uF	G*	G*	G*	G*							M	M	M	M

■ The letter in cell is expressed the symbol of product thickness

■ The letter in cell with "*" mark is expressed capacitance tolerance "J"(±5%) only

Capacitance & Voltage (X7R)

Dielectric		X7R																	
EIA	Size	0402						0603						0805					
Code	VDCW	6.3V	10V	16V	25V	50V	100V	6.3V	10V	16V	25V	50V	100V	6.3V	10V	16V	25V	50V	100V
101	100pF		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
121	120		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
151	150		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
181	180		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
221	220		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
271	270		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
331	330		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
391	390		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
471	470		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
561	560		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
681	680		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
821	820		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
102	1000pF		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
122	1200		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
152	1500		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
182	1800		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
222	2200		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
272	2700		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
332	3300		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
392	3900		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
472	4700		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B
562	5600		N	N	N	N			S	S	S	S	S		B	B	B	B	B
682	6800		N	N	N	N			S	S	S	S	S		B	B	B	B	B
822	8200		N	N	N	N			S	S	S	S	S		B	B	B	B	B
103	0.01μF		N	N	N	N			S	S	S	S	S		B	B	B	B	B
123	0.012		N	N	N				S	S	S	S	X		B	B	B	B	B
153	0.015		N	N	N				S	S	S	S	X		B	B	B	B	B
183	0.018		N	N	N				S	S	S	S	X		B	B	B	B	B
223	0.022		N	N	N				S	S	S	S	X		B	B	B	B	B
273	0.027		N	N	N				S	S	S	S	X		B	B	B	B	D
333	0.033		N	N	N				S	S	S	X	X		B	B	B	B	D
393	0.039		N	N	N				S	S	S	X	X		B	B	B	B	D
473	0.047		N	N	N	N			S	S	S	X	X		B	B	B	B	D
563	0.056		N	N					S	S	S	X	X		B	B	B	B	D
683	0.068		N	N					S	S	S	X	X		B	B	B	B	D
823	0.082		N	N					S	S	S	X	X		B	B	B	B	D
104	0.10μF	N	N	N	N	N			S	S	S	X	X		B	B	B	B	D
124	0.12								S	S	X				B	B	B	D	I
154	0.15								S	S	X				D	D	D	D	I
184	0.18								S	S	X				D	D	D	D	I
224	0.22	N	N	N	N				S	S	X	X			D	D	D	D	I
274	0.27							X	X	X	X				D	D	D	I	
334	0.33							X	X	X	X				D	D	D	I	
394	0.39							X	X	X	X				D	D	D	I	
474	0.47	N	N					X	X	X	X	X			D	D	D	I	I
564	0.56							X	X	X					D	D	D		
684	0.68							X	X	X					D	D	D		
824	0.82							X	X	X					D	D	D		
105	1.0μF	N						X	X	X	X	X			D	D	D	I	
155	1.5														I	I	I	I	
225	2.2							X	X	X				I	I	I	I	I	
335	3.3																		
475	4.7							X						I	I	I	I		
106	10													I	I	I*			

■ The letter in cell is expressed the symbol of product thickness

■ The letter in cell with "*" mark is expressed product not in 10% (code "K") tolerance

Capacitance & Voltage (X7R)

Dielectric		X7R																	
EIA	Size	1206							1210						1812				
Code	VDCW	6.3V	10V	16V	25V	35V	50V	100V	6.3V	10V	16V	25V	50V	100V	10V	16V	25V	50V	100V
151	150 pF		B	B	B		B	B											
181	180		B	B	B		B	B											
221	220		B	B	B		B	B											
271	270		B	B	B		B	B											
331	330		B	B	B		B	B											
391	390		B	B	B		B	B											
471	470		B	B	B		B	B											
561	560		B	B	B		B	B											
681	680		B	B	B		B	B											
821	820		B	B	B		B	B											
102	1000pF		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
122	1200		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
152	1500		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
182	1800		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
222	2200		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
272	2700		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
332	3300		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
392	3900		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
472	4700		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
562	5600		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
682	6800		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
822	8200		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
103	0.01μF		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
123	0.012		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
153	0.015		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
183	0.018		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
223	0.022		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
273	0.027		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
333	0.033		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
393	0.039		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
473	0.047		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
563	0.056		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
683	0.068		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
823	0.082		B	B	B		B	D		C	C	C	C	C	D	D	D	D	D
104	0.10μF		B	B	B		B	D		C	C	C	C	C	D	D	D	D	D
124	0.12		B	B	B		B	D		C	C	C	C	C	D	D	D	D	D
154	0.15		C	C	C		C	G		C	C	C	C	D	D	D	D	D	D
184	0.18		C	C	C		C	G		C	C	C	C	D	D	D	D	D	D
224	0.22		C	C	C		C	G		C	C	C	C	D	D	D	D	D	D
274	0.27		C	C	C		D	G		C	C	C	C	G	D	D	D	D	D
334	0.33		C	C	C		D	G		C	C	C	D	G	D	D	D	D	D
394	0.39		C	C	J		P	G		C	C	C	D	M	D	D	D	D	D
474	0.47		J	J	J		P	G		C	C	C	D	M	D	D	D	D	K
564	0.56		J	J	J		P	P		D	D	D	D	M	D	D	D	D	K
684	0.68		J	J	J		P	P		D	D	D	D	K	D	D	D	K	K
824	0.82		J	J	J		P	P		D	D	D	D	K	D	D	D	K	K
105	1.0μF		J	J	J		P	P		D	D	D	D	K	D	D	D	K	K
155	1.5	J	J	J	P						K	G	M	M					K
225	2.2	J	J	J	P		P	P			K	G	M	M				M	M
335	3.3		P	P	P						K	G	M						
475	4.7	P	P	P	P		P			K	K	K	M	M					
106	10	P	P	P	P	P				K	K	K	M						
226	22	P	P	P*						M	M	M							
476	47								M	M									

■The letter in cell is expressed the symbol of product thickness

■The letter in cell with "*" mark is expressed product not in 10% (code "K") tolerance

Capacitance & Voltage (X5R)

Dielectric		X5R																								
EIA	Size	0402					0603					0805					1206					1210				
Code	VDCW	6.3V	10V	16V	25V	50V	6.3V	10V	16V	25V	50V	6.3V	10V	16V	25V	50V	6.3V	10V	16V	25V	50V	6.3V	10V	16V	25V	50V
273	0.027μF			N																						
333	0.033			N																						
393	0.039			N																						
473	0.047	N	N	N																						
563	0.056	N	N	N																						
683	0.068	N	N	N																						
823	0.082	N	N	N																						
104	0.10μF	N	N	N	N	N																				
154	0.15	N	N	N	N																					
224	0.22	N	N	N	N	N			X	X																
274	0.27							X	X	X																
334	0.33	N	N				X	X	X	X																
394	0.39							X	X	X																
474	0.47	N	N	E	E	E	X	X	X	X	X															
684	0.68	N	N				X	X	X	X																
824	0.82						X	X	X																	
105	1.0μF	N	N	N	N	E	X	X	X	X	X		D	D	D	I										
155	1.5						X					I	I	I	I		J	J					K	K		
225	2.2	N	N	E	E		X	X	X	X	X	I	I	I	I	I	J	J	P	P			K	K		
335	3.3						X	X				I	I	I	I			P	P	P	P					
475	4.7	E*	E*	E*			X	X	X	X		I	I	I	I	I	P	P	P	P	P			K	K	K
685	6.8																P	P								
106	10μF	E*	E*				X	X	X	X*		I	I	I	I	I	P	P	P	P	P	K	K	K	K	M
226	22						X*	X*				I	I*	I*	I*		P	P	P	P		M	M	M	M	
476	47						X*					I*	I*				P	P	P*			M	M	M	M*	
107	100											I*					P					M	M			

■ The letter in cell is expressed the symbol of product thickness

■ The letter in cell with "*" mark is expressed product not in 10% (code "K") tolerance

Capacitance & Voltage (Y5V)

Dielectric		Y5V																																	
EIA	Size	0402					0603					0805					1206						1210							1812					
Code	VDCW	6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	6.3	10	16	25	35	50	100	10	16	25	50	100
103	0.010μF		N	N	N	N		S	S	S	S		A	A	A	A	B		B	B	B	B	B							C					D
153	0.015		N	N	N	N		S	S	S	S		A	A	A	A	B		B	B	B	B	B							C					D
223	0.022		N	N	N	N		S	S	S	S		A	A	A	A	B		B	B	B	B	B							C					D
333	0.033		N	N	N	N		S	S	S	S		A	A	A	A	B		B	B	B	B	B							C					D
473	0.047		N	N	N			S	S	S	S		A	A	A	A	B		B	B	B	B	B							C					D
683	0.068		N	N	N			S	S	S	S		A	A	A	A	B		B	B	B	B	B							C					D
104	0.10μF		N	N	N			S	S	S	S		A	A	A	A	B		B	B	B	B	B		C	C	C		C	C	D	D	D	D	D
154	0.15		N	N				S	S	S	S		A	A	A	A			B	B	B	B	C		C	C	C		C	C	D	D	D	D	D
224	0.22	N	N	N				S	S	S	S		A	A	A	A			B	B	B	B	C		C	C	C		C	C	D	D	D	D	D
334	0.33	N	N	N				S	S	S	X		B	B	B	B			B	B	B	B			C	C	C		C	C	D	D	D	D	D
474	0.47	N	N	N				S	S	X	X		B	B	B	B			B	B	B	B			C	C	C		C		D	D	D	D	D
684	0.68	N						S	X	X			B	B	D	D			B	B	B	B			C	C	C		C		D	D	D	D	D
105	1.0μF	N	N					S	X	X			B	B	D	D			C	C	C	C			C	C	C		C		D	D	D	D	D
155	1.5							S					D	D					C	C	C				C	C	C				D	D	D	D	
225	2.2						S	S	X				D	D	I				C	C	C	J			C	C	C		G		D	D	D	D	
335	3.3												D	D					J	J	J				C	C	C				D	D	D	D	
475	4.7						X	X					D	D	I				J	J	J	P			C	C	D		G		D	D	D	D	
685	6.8												I						J	J					C	C	D		K		D	D	D	D	
106	10μF											I	I	I					J	J	P				D	D	G	K	K		D	D	D	K	
226	22μF											I	I						P	P					K	K									
476	47μF																	P							K	K						M			
107	100μF																								M										

Multilayer Ceramic Chip Capacitor

Environmental Characteristics

Size	0402, 0603, 0805, 1206, 1210, 1812			
Dielectric	NP0	X7R	X5R	Y5V
Capacitance*	0.1pF~0.1μF	100pF~47μF	27nF~100μF	10nF~100μF
Capacitance tolerance	Cap ≤ 5pF: B (±0.1pF), C (±0.25pF) 5pF < Cap < 10pF: C (±0.25pF), D (±0.50pF) Cap ≥ 10pF: J (±5%)	J (± 5%) K (±10%)		M (±20%) Z (-20 / +80%)
Rated voltage (VDCW)	10V, 16V, 25V, 50V, 100V	6.3V, 10V, 16V, 25V, 35V, 50V, 100V		
Q*	Cap < 30pF: Q ≥ 400 +20C Cap ≥ 30pF: Q ≥ 1000	Note 1		
Insulation resistance at Ur**	≥ 10GΩ or R×C ≥ 500Ω×F Whichever is less			
Operating temperature	-55 to +125°C		-55 to 85°C	-25 to +85°C
Capacitance change	±30 ppm	±15%		+30/-80%
Termination	Ni/Sn (lead-free termination)			

■ **Measured at the condition of 30~70% related humidity

■ NP0: Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap ≤ 1000pF and 1.0±0.2Vrms, 1.0 KHz±10% for Cap > 1000pF, 25°C ambient temperature

■ X7R: Apply 1.0±0.2Vrms, 1.0KHz±10% at the condition of 25°C ambient temperature

■ Y5V: Apply 1.0±0.2Vrms, 1.0 KHz±10% at the condition of 20°C ambient temperature

Note 1:

X7R / X5R

Rated Vol.	D.F.	Exception of D.F.	
≥ 100V	≤ 2.5%	≤ 3%	1206 ≥ 0.47μF
		≤ 5%	0805 > 0.1μF; 06030.068μF 1206 > 1μF; 1210 ≥ 2.2μF
		≤ 10%	0805 > 0.22μF; 1210 ≥ 3.3μF
50V	≤ 2.5%	≤ 3%	0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF
		≤ 5%	0201 ≥ 0.01uF; 1210 ≥ 4.7μF
		≤ 10%	0402 ≥ 0.1μF; 0603 > 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF
35V	≤ 3.5%	≤ 10%	0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF
25V	≤ 3.5%	≤ 5%	0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210 ≥ 10μF
		≤ 7%	0603 ≥ 0.33μF; 1206 ≥ 4.7μF
		≤ 10%	0201 ≥ 0.1μF; 0402 ≥ 0.10μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 6.8μF ; 1210 ≥ 22μF
		≤ 12.5%	0402 ≥ 0.47μF
16V	≤ 3.5%	≤ 5%	0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF
		≤ 10%	0201 ≥ 0.1uF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.22uF; 0603 ≥ ; 1206 ≥ 4.7μF; 1210 ≥ 22μF
10V	≤ 5.0%	≤ 10%	0201 ≥ 0.012μF; 0402 ≥ 0.33μF(0402/X7R ≥ 0.22μF); 0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF
		≤ 15%	0201 ≥ 0.1μF
6.3V	≤ 10%	≤ 15%	0201 ≥ 0.1μF; 0402 ≥ 1μF; 0603 ≥ 10μF; 0805 ≥ 4.7μF; 1206 ≥ 47μF ; 1210 ≥ 100μF
		≤ 20%	0402 ≥ 2.2μF

Y5V

Rated vol.	D.F.	Exception of D.F.	
≥ 50V	≤ 5%	≤ 7%	0603 ≥ 0.1μF; 0805 ≥ 0.47μF; 1206 ≥ 4.7μF
		≤ 12.5%	1210 ≥ 6.8μF
35V	≤ 7%	---	---
25V	≤ 5%	≤ 7%	0402 ≥ 0.047μF; 0603 ≥ 0.1μF; 0805 ≥ 0.33μF; 1206 ≥ 1μF; 1210 ≥ 4.7μF
		≤ 9%	0402 ≥ 0.068μF; 0603 ≥ 0.47μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF
16V (C < 1.0μF)	≤ 7%	≤ 9%	0402 ≥ 0.068μF; 0603 ≥ 0.68μF
		≤ 12.5%	0402 ≥ 0.22μF
16V (C ≥ 1.0μF)	≤ 9%	≤ 12.5%	0603 ≥ 2.2μF; 0805 ≥ 3.3μF; 1206 ≥ 10μF; 1210 ≥ 22μF; 1812 ≥ 47μF
10V	≤ 12.5%	≤ 20%	0402 ≥ 0.47μF
6.3V	≤ 20%	---	---

■ Middle and High Voltage

Capacitance & Voltage (NPO 200V~3KV)

Dielectric		NPO																													
EIA	Size	0603		0805				1206						1210						1808					1812						
Code	VDCW	200	250	200	250	500 630	1000	200	250	500	630	1000	1500 2000	200	250	500	630	1000	1500 2000	500 630	1000	1500	2000	3000	200	250	500 630	1000	1500	2000	3000
0R5	0.5pF	S	S	A	A	A	D																								
1R0	1.0	S	S	A	A	A	D																								
1R2	1.2	S	S	A	A	A	D																								
1R5	1.5	S	S	A	A	A	D	B	B	B	B	B	B																		
1R8	1.8	S	S	A	A	A	D	B	B	B	B	B	B							D											
2R2	2.2	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
2R7	2.7	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
3R3	3.3	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
3R9	3.9	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
4R7	4.7	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
5R6	5.6	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
6R8	6.8	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
8R2	8.2	S	S	A	A	A	D	B	B	B	B	B	B							D	D	D	D	D							
100	10pF	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
120	12	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
150	15	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
180	18	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
220	22	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
270	27	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
330	33	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
390	39	S	S	A	A	A	D	B	B	B	B	B	B	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
470	47	S	S	A	A	A	D	B	B	B	B	B	C	C	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
560	56	S	S	A	A	A	D	B	B	B	B	B	C	D	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
680	68	S	S	A	A	A	D	B	B	B	B	B	C	D	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
820	82	S	S	A	A	B	D	B	B	B	B	B	D	D	C	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D
101	100pF	S	S	A	B	B	D	B	B	B	B	B	D	D	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D	D
121	120	S	S	A	B	D	D	B	B	B	B	B	D	G	C	C	C	C	C	D	D	D	D	D	D	D	D	D	D	D	D
151	150	S	S	B	D	D	D	B	B	B	B	B	D	G	C	C	C	C	C	D	G	D	D	K	K	K	D	D	D	D	D
181	180	S	S	B	D	D	D	B	B	B	B	B	G	G	C	C	C	C	C	D	G	D	D	K	K	K	D	D	D	D	K
221	220	S	S	D	D	D	D	B	B	B	B	B	G	G	C	C	C	C	G	G	D	D	K	K	K	D	D	D	D	D	K
271	270	X	X	D	D	D	D	B	C	C	C	C	G	P	C	C	C	C	G	K	K	K	K	K	K	D	D	D	D	K	K
331	330	X	X	D	D	D	D	B	C	C	C	C	G	P	C	C	C	C	G	K	K	K	K	K	K	D	D	D	D	K	K
391	390	X	X	D	D	D	D	B	C	C	C	C	G	P	C	C	C	C	G	M	K	K	K	K		D	D	D	D	K	K
471	470	X	X	D	D	I		C	C	C	C	G			C	C	C	C	G	M	K	K	K	K		D	D	D	K	K	K
561	560			D	D	I		C	D	D	D	D	G		C	C	C	C	G		K	K	K	K		D	D	D	K	K	K
681	680			D	D	I		C	D	D	D	D	G		C	C	C	C	G		K	K	K	K		D	D	D	K	K	K
821	820			D	D	I		C	G	G	G	G	G		C	C	C	C	G		K	K				D	D	D	K	K	K
102	1000pF			D	D	I		C	G	G	G	G	G		D	D	D	D	G		K	K				D	D	D	K	K	K
122	1200			D	D			C	G	G	G	G			D	D	D	D			K					D	D	D	K		
152	1500			D	D			D	G	G	G				D	D	D	D			K					D	D	D	K		
182	1800			D	D			D	G	G	G				D	D	D	D			K					D	D	D			
222	2200			D	D			D	G	G	G				D	D	D	D			K					D	D	D			
272	2700							D	G						D	D	D	D								D	D	D			
332	3300							D	G						D	D	D	D								D	D	D			
392	3900							D	G						D	D	D	D								D	D				
472	4700							D	G						G	G										D	D				
562	5600														G	G										D	D				
682	6800														G	G										D	D				
822	8200														G	G															
103	0.01uF														G	G															

■ The letter in cell is expressed the symbol of product thickness

Capacitance & Voltage (X7R 200V~3KV)

Dielectric		X7R																									
EIA	Size	0603	0805				1206					1210				1808					1812						
Code	VDCW	200V 250V	200V	250V	500V 630V	1000V	200V 250V	500V 630V	1000V	1500V	2000V	200V 250V	500V 630V	1000V	1500V 2000V	500V 630V	1000V	1500V 2000V	3000V	200V 250V	500V 630V	1000V	1500V 2000V	3000V			
101	100pF	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	D								
121	120	X	B	B	B	B	D	D	D	D	D	D	D	D	D												
151	150	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	D								
181	180	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	D								
221	220	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	D								
271	270	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	D				D	D	K		
331	330	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	K				D	D	K		
391	390	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	K				D	D	K		
471	470	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	K				D	D	K		
561	560	X	B	B	B	B	D	D	D	D	D	D	D	D	D	D	D	D	K				D	D	K		
681	680	X	B	B	B	B	D	D	D	D	D	C	D	D	D	D	D	D	K				D	D	K		
821	820	X	B	B	B	B	D	D	D	D	D	C	D	D	D	D	D	D	K				D	D	K		
102	1000pF	X	B	B	B	B	D	D	D	D	D	C	D	D	D	D	D	K	K	D	D	D	D	D	K		
122	1200	X	B	B	B	B	D	D	D	G	G	C	D	D	M	D	D	K	K	D	D	D	D	D	K		
152	1500	X	B	B	B	D	D	D	D	G	G	C	D	D	M	D	D	K	K	D	D	D	D	D	K		
182	1800	X	B	B	B	D	D	D	D	G	G	C	D	D	M	D	D	K	K	D	D	D	D	G	M		
222	2200	X	B	B	B	D	D	D	D	G	G	C	D	D	M	D	D	K		D	D	D	D	G	M		
272	2700	X	B	B	B		D	D	D	G	G	C	D	D	M	D	D	K		D	D	D	D	G	M		
332	3300	X	B	B	B		D	D	D	G	G	C	D	D	M	D	D	K		D	D	D	D	K	M		
392	3900	X	B	B	B		D	D	D	G		C	D	G	M	D	D	K		D	D	D	D	K			
472	4700	X	B	B	D		D	D	D	G		C	D	G	M	D	D	K		D	D	D	D	K			
562	5600	X	D	D	D		D	D	D	G		C	D	G		K	K	K		D	D	D	D	M			
682	6800	X	D	D	D		D	D	D	G		C	D	G		K	K			D	D	D	D	M			
822	8200	X	D	D	D		D	D	D			C	D	G		K	K			D	D	D	D	M			
103	0.010μF	X	D	D	D		D	D	D			C	D	G		K	K			D	D	D	D	M			
123	0.012		D	D	D		D	D	G			C	D	G		K	K			D	D	K					
153	0.015		D	D	D		D	D	G			C	D	G		K	K			D	D	K					
183	0.018		D	D	D		D	D				C	D	G		K	K			D	D	M					
223	0.022		D	D	D		D	G				C	D	G		K	K			D	D	M					
273	0.027		D	D			D	G				C	G			K	K			D	D	M					
333	0.033		D	D			G	G				C	G			K	K			D	D	M					
393	0.039		D	D			G	G				C	G			K	K			D	D	M					
473	0.047		D	D			G	G				D	G			K	K			D	D	M					
563	0.056		D	D			G	G				D	G			K				D	K	M					
683	0.068		D				G					G	K			K				D	K	M					
823	0.082		D				G					G	K							D	K	M					
104	0.10μF		D				G					G	K							D	K	M					
124	0.12											G								D	M						
154	0.15											M								K	M						
184	0.18											M								K	M						
224	0.22											M								K	M						
274	0.27											M								K							
334	0.33											M								K							
394	0.39											M								K							
474	0.47											M								K							
564	0.56																			M							
684	0.68																			M							
824	0.82																			M							
105	1μF																			M							

■ The letter in cell is expressed the symbol of product thickness

Capacitance & Voltage (Y5V 200V~250V)

Dielectric		Y5V							
EIA	Size	0805		1206		1210		1812	
Code	VDCW	200	250	200	250	200	250	200	250
103	0.010μF	B	B	B	B	C	C	D	D
153	0.015	B	B	B	B	C	C	D	D
223	0.022	B	B	B	B	C	C	D	D
333	0.033	B	B	B	B	C	C	D	D
473	0.047	B	B	B	B	C	C	D	D
683	0.068	B	B	B	B	C	C	D	D
104	0.10μF			B	B	C	C	D	D
154	0.15			C	C	C	C	D	D
224	0.22							D	D
334	0.33							D	D
474	0.47							D	D
684	0.68							D	D

■ The letter in cell is expressed the symbol of product thickness

Electrical data

Dielectric	NP0	X7R	Y5V
Size	0603,0805,1206,1210,1808,1812		0805,1206,1210,1812
Capacitance*	0.5pF~0.01μF		0.01uF~0.68μF
Capacitance tolerance	Cap ≤ 5pF: C (±0.25pF) 5pF < Cap < 10pF: D (±0.50pF) Cap ≥ 10pF: J (±5%), K (±10%)		K (±10%) M (±20%) Z (-20 / +80%)
Rated voltage (VDCW)	200V to 3KV		200V, 250V
DF/Q	Cap < 30pF: Q ≥ 400 +20C Cap ≥ 30pF: Q ≥ 1000		DF ≤ 2.5% DF ≤ 5%
Insulation resistance at Ur	Ur=200~630V: ≥ 10GΩ or R×C ≥ 100Ω·F Whichever is smaller Ur=1000~3000V: ≥ 10GΩ		
Dielectric Strength	200~300V: ≥ 2×VDCW 500~999V: ≥ 1.5×VDCW 1000~3000V: ≥ 1.2×VDCW		
Operating temperature	-55 to +125°C		-25 to +85°C
Capacitance change	±30 ppm		±15% +30/-80%
Termination	Ni/Sn (lead-free termination)		

■ **Measured at the condition of 30~70% related humidity

■ NP0: Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap ≤ 1000pF and 1.0±0.2Vrms, 1.0KHz±10% for Cap > 1000pF, 25°C ambient temperature

■ X7R, X5R: Apply 1.0±0.2Vrms, 1.0KHz±10% at the condition of 25°C ambient temperature

■ Y5V: Apply 1.0±0.2Vrms, 1.0KHz±10% at the condition of 20°C ambient temperature

■ Ultra-small 0201 Capacitors

Capacitance & Voltage

EIA	Size	0201		
		NPO		
Code	VDCW	16V	25V	50V
0R1	0.1pF	L	L	L
0R2	0.2	L	L	L
0R3	0.3	L	L	L
0R4	0.4	L	L	L
0R5	0.5	L	L	L
0R6	0.6	L	L	L
0R7	0.7	L	L	L
0R8	0.8	L	L	L
0R9	0.9	L	L	L
1R0	1.0	L	L	L
1R2	1.2	L	L	L
1R5	1.5	L	L	L
1R8	1.8	L	L	L
2R2	2.2	L	L	L
2R7	2.7	L	L	L
3R0	3.0	L	L	L
3R3	3.3	L	L	L
3R9	3.9	L	L	L
4R0	4.0	L	L	L
4R7	4.7	L	L	L
5R0	5.0	L	L	L
5R6	5.6	L	L	L
6R0	6.0	L	L	L
6R8	6.8	L	L	L
7R0	7.0	L	L	L
8R2	8.2	L	L	L
9R0	9.0	L	L	L
100	10	L	L	L
120	12	L	L	L
150	15	L	L	L
180	18	L	L	L
220	22	L	L	L
270	27	L	L	L
330	33	L	L	L
390	39	L	L	L
470	47	L	L	L
560	56	L	L	L
680	68	L	L	L
820	82	L	L	L
101	100	L	L	L
121	120	L	L	L
151	150		L	L
271	270		L	
331	330		L	
391	390		L	
471	470		L	
561	560		L	

EIA	Size	0201									
		X7R					X5R				
Code	VDCW	6.3V	10V	16V	25V	50V	6.3V	10V	16V	25V	50V
101	100pF			L	L	L			L	L	L
121	120			L	L	L			L	L	L
151	150			L	L	L			L	L	L
181	180			L	L	L			L	L	L
221	220			L	L	L			L	L	L
271	270			L	L	L			L	L	L
331	330			L	L	L			L	L	L
391	390			L	L	L			L	L	L
471	470			L	L	L			L	L	L
561	560			L	L	L			L	L	L
681	680			L	L	L			L	L	L
821	820			L	L	L			L	L	L
102	1000	L	L	L	L	L		L	L	L	L
122	1200	L	L	L	L						
152	1500	L	L	L	L			L	L		
182	1800	L	L	L							
222	2200	L	L	L				L	L		
272	2700	L	L	L				L	L		
332	3300	L	L	L	L			L	L		
392	3900	L	L	L							
472	4700	L	L	L				L	L		
562	5600	L	L								
682	6800	L	L					L			
822	8200	L	L								
103	0.010μF	L	L	L	L		L	L	L	L	L
153	0.015						L	L			
223	0.022		L				L	L			
273	0.027						L	L			
333	0.033						L	L			
393	0.039						L	L			
473	0.047						L	L	L		
563	0.056						L	L			
683	0.068						L	L			
823	0.082						L	L			
104	0.100						L	L	L	L	
224	0.220						L	L	L*		
474	0.470						L				
105	1μF						L	L*			
225	2.2						L*	L*			

■ The letter in cell is expressed the symbol of product thickness

■ The letter in cell with "*" mark is expressed capacitance tolerance "K"(±10%) only

Electrical Data

Size	0201		
	NPO	X7R	X5R
Capacitance*	0.1pF~560pF	100pF~22nF	100pF~2.2μF
Capacitance tolerance	Cap ≤ 5pF: C (±0.25pF) 5pF < Cap < 10pF: D (±0.50pF) Cap ≥ 10pF: J (±5%)	J (±5%) K (±10%)	K (±10%) M (±20%)
Rated voltage (VDCW)	16V, 25V, 50V	6.3V, 10V, 16V, 25V, 50V	6.3V, 10V, 16V, 25V, 50V
Operating temperature	-55 to +125°C		-55 to +85°C
Capacitance change	±30 ppm	±15%	
Termination	Ni/Sn (lead-free termination)		

■ **Measured at 30~70% related humidity

■ NPO: Apply 1.0±0.2Vrms, 1.0MHz±10% at the condition of 25°C ambient temperature

■ X7R, X5R: Apply 1.0±0.2Vrms, 1.0KHz±10% at the condition of 25°C ambient temperature

■ Ultra High Q & Low ESR Capacitors for MCRF Series

Capacitance & Voltage

Dielectric		NPO														
EIA	Size	0201				0402				0603			0805			
Code	VDCW	6.3V	10V	25V	50V	25V	50V	100V	200V	50V	100V	250V	50V	100V	250V	500V
0R1	0.1pF	L	L	L	L	N	N	N	N							
0R2	0.2	L	L	L	L	N	N	N	N							
0R3	0.3	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
0R4	0.4	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
0R5	0.5	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
0R6	0.6	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
0R7	0.7	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
0R8	0.8	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
0R9	0.9	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
1R0	1.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
1R2	1.2	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
1R5	1.5	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
1R8	1.8	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
2R0	2.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
2R2	2.2	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
2R7	2.7	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
3R0	3.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
3R3	3.3	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
3R9	3.9	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
4R0	4.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
4R7	4.7	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
5R0	5.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
5R6	5.6	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
6R0	6.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
6R8	6.8	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
7R0	7.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
8R2	8.2	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
9R0	9.0	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
100	10	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
110	11	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
120	12	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
130	13	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
150	15	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
160	16	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
180	18	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
200	20	L	L	L	L	N	N	N	N	S	S	S	T	T	T	T
220	22	L	L	L		N	N	N	N	S	S	S	T	T	T	T
240	24	L	L	L		N	N	N	N	S	S	S	T	T	T	T
270	27	L	L	L		N	N	N	N	S	S	S	T	T	T	T
300	30	L	L	L		N	N	N	N	S	S	S	T	T	T	T
330	33	L	L	L		N	N	N		S	S	S	T	T	T	T
360	36					N	N	N		S	S	S	T	T	T	T
390	39					N	N	N		S	S	S	T	T	T	T
430	43					N	N	N		S	S	S	T	T	T	T
470	47					N	N	N		S	S	S	T	T	T	T
560	56					N				S	S	S	T	T	T	T
680	68					N				S	S	S	T	T	T	T
820	82					N				S	S	S	T	T	T	
101	100					N				S	S	S	T	T	T	

■ The letter in cell is expressed the symbol of product thickness



Electrical Data

Dielectric	NPO
Size	0201, 0402, 0603, 0805
Capacitance*	0201: 0.1pF ~ 33pF, 0402: 0.1pF ~ 100pF 0603: 0.3pF ~ 100pF, 0805: 0.3pF ~ 100pF
Capacitance tolerance**	Cap ≤ 5pF: A(±0.05pF), B(±0.1pF), C(±0.25pF) 5pF < Cap < 10pF: B(±0.1pF), C(±0.25pF), D(±0.5pF) Cap ≥ 10pF: F(±1%), G(±2%), J(±5%)
Rated voltage (VDCW)	6.3V, 10V, 25V, 50V, 100V, 250V, 500V
Q *	Cap ≥ 30pF: Q ≥ 1000, Cap < 30pF: Q ≥ 400+20C;
Insulation resistance at Ur	≥ 10GΩ
Operating temperature	-55 to +125°C
Capacitance	±30 ppm; 0201 Cap ≥ 22pF, ±60 ppm
Termination	Ni/Sn (lead-free termination)

■ **Measured at the conditions of 25°C ambient temperature and 30~70% related humidity

■ Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap ≤ 1000pF; 1.0KHz±10% for Cap > 1000pF

Electrical characteristics



■ Low Inductance Capacitors for MCLI Series

Capacitance & Voltage

Dielectric		X7R
EIA	Size	0612
Code	VDCW	50V
103	10nF	B
123	12	B
153	15	B
183	18	B
223	22	B
273	27	B
333	33	B
393	39	B
473	47	B
563	56	B
683	68	B
823	82	B
104	100	B
124	120	B
154	150	B

■ The letter in cell is expressed the symbol of product thickness

General Electrical data

Size	0612
Dielectric	X7R
Capacitance*	10nF~150nF
Capacitance tolerance	K (±10%) M (±20%)
Rated voltage (WVDC)	50V
Tan δ *	≤ 2.5%
Insulation resistance at Ur	≥ 10GΩ or R×C ≥ 500Ω×F Whichever is less
Operating temperature	-55 to +125°C
Capacitance change	±15%
Termination	Ni/Sn (lead-free termination)
ESL	500pH

■ **Measured at 1.0±0.2Vrms, 1.0KHz±10%, 30~70% related humidity, 25°C ambient temperature

Multilayer Ceramic Chip Capacitor

Environmental Characteristics

Item	Requirement	Test Method																																																													
External Appearance	No defects which may affect performance	Visual inspection & Dimension measurement																																																													
Capacitance(Cap.)	Within the specified tolerance that refers on page2	NPO: (Class I) Cap≤ 1000pF 1.0±0.2Vrms, 1MHz±10% Cap>1000pF 1.0±0.2Vrms, 1KHz±10%																																																													
Dissipation Factor (D.F.) or Quality factor (Q=1/D.F.)	NPO: Cap≥ 30pF, Q≥ 1000; Cap<30pF, Q≥ 400+20C X7R, X5R: <table border="1"> <thead> <tr> <th>Rated vol.</th><th>D.F. ≤</th><th>Exception of D.F. ≤</th></tr> </thead> <tbody> <tr> <td rowspan="3">≥ 100V</td><td rowspan="3">2.5%</td><td>3% 1206 ≥ 0.047μF</td></tr> <tr> <td>5% 0603 ≥ 0.068μF; 0805 ≥ 0.1μF 1206 ≥ 1μF; 1210 ≥ 2.2μF</td></tr> <tr> <td>10% 0805 ≥ 0.22μF; 1210 ≥ 3.3μF</td></tr> <tr> <td rowspan="3">50V</td><td rowspan="3">2.5%</td><td>3% 0201(50V); 0603 ≥ 0.047μF 0805 ≥ 0.18μF; 1206 ≥ 0.47μF</td></tr> <tr> <td>5% 0201 ≥ 0.01μF; 1210 ≥ 4.7μF</td></tr> <tr> <td>10% 0402 ≥ 0.1μF; 0603 ≥ 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF</td></tr> <tr> <td>35V</td><td>3.5%</td><td>10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF</td></tr> <tr> <td rowspan="4">25V</td><td rowspan="4">3.5%</td><td>5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210 ≥ 10μF</td></tr> <tr> <td>7% 0603 ≥ 0.33μF; 1206 ≥ 4.7μF</td></tr> <tr> <td>10% 0201 ≥ 0.1μF; 0402 ≥ 0.10μF; 0603 ≥ 0.47μF 0805 ≥ 2.2μF; 1206 ≥ 6.8μF; 1210 ≥ 22μF</td></tr> <tr> <td>12.5% 0402 ≥ 0.47μF</td></tr> <tr> <td rowspan="2">16V</td><td rowspan="2">3.5%</td><td>5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF</td></tr> <tr> <td>10% 0201 ≥ 0.1μF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.22μF; 0603 ≥ 0.68μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF</td></tr> <tr> <td rowspan="2">10V</td><td rowspan="2">5%</td><td>10% 0201 ≥ 0.012μF; 0402 ≥ 0.33μF(0402/X7R ≥ 0.22μF) 0603 ≥ 0.33μF; 0805 ≥ 2.2μF 1206 ≥ 2.2μF; 1210 ≥ 22μF</td></tr> <tr> <td>15% 0201 ≥ 0.1μF; 0402 ≥ 1μF</td></tr> <tr> <td rowspan="2">6.3V</td><td rowspan="2">10%</td><td>15% 0201 ≥ 0.1μF; 0402 ≥ 1μF 0603 ≥ 10μF; 0805 ≥ 4.7μF 1206 ≥ 47μF; 1210 ≥ 100μF</td></tr> <tr> <td>20% 0402 ≥ 2.2μF</td></tr> </tbody> </table> Y5V: <table border="1"> <thead> <tr> <th>Rated vol.</th><th>D.F. ≤</th><th>Exception of D.F. ≤</th></tr> </thead> <tbody> <tr> <td rowspan="2">≥ 50V</td><td rowspan="2">5%</td><td>7% 0603 ≥ 0.1μF; 0805 ≥ 0.47μF; 1206 ≥ 4.7μF</td></tr> <tr> <td>12.5% 1210 ≥ 6.8μF</td></tr> <tr> <td>35V</td><td>7%</td><td>—</td></tr> <tr> <td rowspan="2">25V</td><td rowspan="2">5%</td><td>7% 0402 ≥ 0.047μF; 0603 ≥ 0.1μF 0805 ≥ 0.33μF; 1206 ≥ 1μF 1210 ≥ 4.7μF</td></tr> <tr> <td>9% 0402 ≥ 0.068μF; 0603 ≥ 0.47μF 1206 ≥ 4.7μF; 1210 ≥ 22μF</td></tr> <tr> <td rowspan="2">16V (C < 1.0μF)</td><td rowspan="2">7%</td><td>9% 0402 ≥ 0.068μF; 0603 ≥ 0.68μF</td></tr> <tr> <td>12.5% 0402 ≥ 0.22μF</td></tr> <tr> <td>16V (C ≥ 1.0μF)</td><td>9%</td><td>12.5% 0603 ≥ 2.2μF; 0805 ≥ 3.3μF 1206 ≥ 10μF; 1210 ≥ 22μF 1812 ≥ 47μF</td></tr> <tr> <td>10V</td><td>12.5%</td><td>20% 0402 ≥ 0.47μF</td></tr> <tr> <td>6.3V</td><td>20%</td><td>-</td></tr> </tbody> </table>	Rated vol.	D.F. ≤	Exception of D.F. ≤	≥ 100V	2.5%	3% 1206 ≥ 0.047μF	5% 0603 ≥ 0.068μF; 0805 ≥ 0.1μF 1206 ≥ 1μF; 1210 ≥ 2.2μF	10% 0805 ≥ 0.22μF; 1210 ≥ 3.3μF	50V	2.5%	3% 0201(50V); 0603 ≥ 0.047μF 0805 ≥ 0.18μF; 1206 ≥ 0.47μF	5% 0201 ≥ 0.01μF; 1210 ≥ 4.7μF	10% 0402 ≥ 0.1μF; 0603 ≥ 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF	35V	3.5%	10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF	25V	3.5%	5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210 ≥ 10μF	7% 0603 ≥ 0.33μF; 1206 ≥ 4.7μF	10% 0201 ≥ 0.1μF; 0402 ≥ 0.10μF; 0603 ≥ 0.47μF 0805 ≥ 2.2μF; 1206 ≥ 6.8μF; 1210 ≥ 22μF	12.5% 0402 ≥ 0.47μF	16V	3.5%	5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF	10% 0201 ≥ 0.1μF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.22μF; 0603 ≥ 0.68μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF	10V	5%	10% 0201 ≥ 0.012μF; 0402 ≥ 0.33μF(0402/X7R ≥ 0.22μF) 0603 ≥ 0.33μF; 0805 ≥ 2.2μF 1206 ≥ 2.2μF; 1210 ≥ 22μF	15% 0201 ≥ 0.1μF; 0402 ≥ 1μF	6.3V	10%	15% 0201 ≥ 0.1μF; 0402 ≥ 1μF 0603 ≥ 10μF; 0805 ≥ 4.7μF 1206 ≥ 47μF; 1210 ≥ 100μF	20% 0402 ≥ 2.2μF	Rated vol.	D.F. ≤	Exception of D.F. ≤	≥ 50V	5%	7% 0603 ≥ 0.1μF; 0805 ≥ 0.47μF; 1206 ≥ 4.7μF	12.5% 1210 ≥ 6.8μF	35V	7%	—	25V	5%	7% 0402 ≥ 0.047μF; 0603 ≥ 0.1μF 0805 ≥ 0.33μF; 1206 ≥ 1μF 1210 ≥ 4.7μF	9% 0402 ≥ 0.068μF; 0603 ≥ 0.47μF 1206 ≥ 4.7μF; 1210 ≥ 22μF	16V (C < 1.0μF)	7%	9% 0402 ≥ 0.068μF; 0603 ≥ 0.68μF	12.5% 0402 ≥ 0.22μF	16V (C ≥ 1.0μF)	9%	12.5% 0603 ≥ 2.2μF; 0805 ≥ 3.3μF 1206 ≥ 10μF; 1210 ≥ 22μF 1812 ≥ 47μF	10V	12.5%	20% 0402 ≥ 0.47μF	6.3V	20%	-	X7R, X5R, Y5V: (Class II) Cap≤10uF 1.0±0.2Vrms, 1KHz±10%** Cap>10uF 0.5±0.2Vrms, 120Hz±10% ** Test condition: 0.5±0.2Vrms , 1KHz±10% X7R: 0805=106(6.3V,10V), 0603/475(6.3V) X5R: 0201 ≥ 224 (6.3V,10V,16V)#1 0402 ≥ 475 (6.3V,16V), 0402 ≥ 225(10V) 0603=106 (6.3V,10V), #1 Excluding X5R/0201/105(6.3V);225(10V), (1.0±0.2Vrms , 1KHz±10%) *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.
Rated vol.	D.F. ≤	Exception of D.F. ≤																																																													
≥ 100V	2.5%	3% 1206 ≥ 0.047μF																																																													
		5% 0603 ≥ 0.068μF; 0805 ≥ 0.1μF 1206 ≥ 1μF; 1210 ≥ 2.2μF																																																													
		10% 0805 ≥ 0.22μF; 1210 ≥ 3.3μF																																																													
50V	2.5%	3% 0201(50V); 0603 ≥ 0.047μF 0805 ≥ 0.18μF; 1206 ≥ 0.47μF																																																													
		5% 0201 ≥ 0.01μF; 1210 ≥ 4.7μF																																																													
		10% 0402 ≥ 0.1μF; 0603 ≥ 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF																																																													
35V	3.5%	10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF																																																													
25V	3.5%	5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210 ≥ 10μF																																																													
		7% 0603 ≥ 0.33μF; 1206 ≥ 4.7μF																																																													
		10% 0201 ≥ 0.1μF; 0402 ≥ 0.10μF; 0603 ≥ 0.47μF 0805 ≥ 2.2μF; 1206 ≥ 6.8μF; 1210 ≥ 22μF																																																													
		12.5% 0402 ≥ 0.47μF																																																													
16V	3.5%	5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF																																																													
		10% 0201 ≥ 0.1μF(0201/X7R ≥ 0.022μF); 0402 ≥ 0.22μF; 0603 ≥ 0.68μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF																																																													
10V	5%	10% 0201 ≥ 0.012μF; 0402 ≥ 0.33μF(0402/X7R ≥ 0.22μF) 0603 ≥ 0.33μF; 0805 ≥ 2.2μF 1206 ≥ 2.2μF; 1210 ≥ 22μF																																																													
		15% 0201 ≥ 0.1μF; 0402 ≥ 1μF																																																													
6.3V	10%	15% 0201 ≥ 0.1μF; 0402 ≥ 1μF 0603 ≥ 10μF; 0805 ≥ 4.7μF 1206 ≥ 47μF; 1210 ≥ 100μF																																																													
		20% 0402 ≥ 2.2μF																																																													
Rated vol.	D.F. ≤	Exception of D.F. ≤																																																													
≥ 50V	5%	7% 0603 ≥ 0.1μF; 0805 ≥ 0.47μF; 1206 ≥ 4.7μF																																																													
		12.5% 1210 ≥ 6.8μF																																																													
35V	7%	—																																																													
25V	5%	7% 0402 ≥ 0.047μF; 0603 ≥ 0.1μF 0805 ≥ 0.33μF; 1206 ≥ 1μF 1210 ≥ 4.7μF																																																													
		9% 0402 ≥ 0.068μF; 0603 ≥ 0.47μF 1206 ≥ 4.7μF; 1210 ≥ 22μF																																																													
16V (C < 1.0μF)	7%	9% 0402 ≥ 0.068μF; 0603 ≥ 0.68μF																																																													
		12.5% 0402 ≥ 0.22μF																																																													
16V (C ≥ 1.0μF)	9%	12.5% 0603 ≥ 2.2μF; 0805 ≥ 3.3μF 1206 ≥ 10μF; 1210 ≥ 22μF 1812 ≥ 47μF																																																													
10V	12.5%	20% 0402 ≥ 0.47μF																																																													
6.3V	20%	-																																																													
Dielectric Strength	No evidence of damage or flash over during test	To apply voltage(≤ 100V) 250% Duration: 1 to 5sec Charge and discharge current less than 50mA To apply voltage: 200V~300V ≥ 2 time VDC 500V~999V ≥ 1.5 time VDC 1000V~3000V ≥ 1.2 time VDC Cut-off, set at 10mA TEST=15 sec. RAMP=0																																																													

Item	Requirement	Test Method																																														
Insulation Resistance	10GΩ or R×C≥ 500Ω-F Whichever is smaller X7R, X5R, Y5V:	To apply rated voltage for max. 120sec *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.																																														
	<table><tr><td>Rated Voltage</td><td>Insulation Resistance</td></tr><tr><td>100V: X7R</td><td rowspan="6">10GΩ or RxC ≥ 100Ω-F Whichever is smaller</td></tr><tr><td>50V: 0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF</td></tr><tr><td>35V: 0805≥2.2μF;1206≥ 2.2μF;1210≥ 10μF</td></tr><tr><td>25V: 0402≥1uF;0603≥2.2uF;0805≥2.2uF1206≥10uF;1210≥10uF</td></tr><tr><td>16V: 0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF;1206≥10μF;1210≥47μF</td></tr><tr><td>10V: 0201≥47nF;0402≥0.47uF;0603≥0.47uF0805≥2.2uF;1206≥4.7uF;1210≥47uF</td></tr><tr><td>6.3V</td></tr></table>		Rated Voltage	Insulation Resistance	100V: X7R	10GΩ or RxC ≥ 100Ω-F Whichever is smaller	50V: 0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF	35V: 0805≥2.2μF;1206≥ 2.2μF;1210≥ 10μF	25V: 0402≥1uF;0603≥2.2uF;0805≥2.2uF1206≥10uF;1210≥10uF	16V: 0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF;1206≥10μF;1210≥47μF	10V: 0201≥47nF;0402≥0.47uF;0603≥0.47uF0805≥2.2uF;1206≥4.7uF;1210≥47uF	6.3V																																				
	Rated Voltage		Insulation Resistance																																													
	100V: X7R		10GΩ or RxC ≥ 100Ω-F Whichever is smaller																																													
50V: 0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF																																																
35V: 0805≥2.2μF;1206≥ 2.2μF;1210≥ 10μF																																																
25V: 0402≥1uF;0603≥2.2uF;0805≥2.2uF1206≥10uF;1210≥10uF																																																
16V: 0201≥0.1μF;0402≥0.22μF;0603≥1μF;0805≥2.2μF;1206≥10μF;1210≥47μF																																																
10V: 0201≥47nF;0402≥0.47uF;0603≥0.47uF0805≥2.2uF;1206≥4.7uF;1210≥47uF																																																
6.3V																																																
≥ 10GΩ or 100Ω -F whichever is smaller Rated voltage: 200V~630V	To apply rated voltage(500V max.) for 60sec.																																															
≥ 10GΩ Rated voltage: >630V	To apply 500V for 60sec.																																															
Temperature Characteristic of Capacitance	<table><tr><td>T.C.</td><td>Capacitance Change</td></tr><tr><td>NPO</td><td>±30 (ppm/°C)</td></tr><tr><td>X7R</td><td>±15%</td></tr><tr><td>X5R</td><td>±15%</td></tr><tr><td>Y5V</td><td>+30%~-80%</td></tr></table>	T.C.	Capacitance Change	NPO	±30 (ppm/°C)	X7R	±15%	X5R	±15%	Y5V	+30%~-80%	With no electrical load. <table><tr><td>T.C.</td><td>Operating Temp</td></tr><tr><td>NPO</td><td>-55 ~ 125°C at 25°C</td></tr><tr><td>X7R</td><td>-55 ~ 125°C at 25°C</td></tr><tr><td>X5R</td><td>-55 ~ 85°C at 25°C</td></tr><tr><td>Y5V</td><td>-25 ~ 85°C at 20°C</td></tr></table> *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement voltage for Class II: <table><tr><td>0201</td><td>0402</td></tr><tr><td>Cap<0.1μF:1V</td><td>Cap<1μF: 1V</td></tr><tr><td>0.1μF≤Cap<1μF: 0.2V</td><td>Cap=1μF: 0.5V</td></tr><tr><td>Cap≥1μF: 0.1V</td><td>1μF<Cap<10μF: 0.2V</td></tr><tr><td></td><td>Cap≥10μF: 0.1V</td></tr><tr><td>0603</td><td>0805</td></tr><tr><td>Cap≤1μF: 1V</td><td>Cap<10μF: 1V</td></tr><tr><td>1μF<Cap≤4.7μF: 0.5V</td><td>Cap=10μF: 0.5V</td></tr><tr><td>Cap>4.7μF: 0.2V</td><td>Cap>10μF: 0.2V</td></tr><tr><td>1206</td><td>1210</td></tr><tr><td>Cap≤10μF: 1V</td><td>Cap≤10μF: 1V</td></tr><tr><td>10μF<Cap≤100μF: 0.5V</td><td>10μF<Cap≤100μF: 0.5V</td></tr><tr><td>Cap>100μF: 0.2V</td><td>Cap>100μF: 0.2V</td></tr></table>	T.C.	Operating Temp	NPO	-55 ~ 125°C at 25°C	X7R	-55 ~ 125°C at 25°C	X5R	-55 ~ 85°C at 25°C	Y5V	-25 ~ 85°C at 20°C	0201	0402	Cap<0.1μF:1V	Cap<1μF: 1V	0.1μF≤Cap<1μF: 0.2V	Cap=1μF: 0.5V	Cap≥1μF: 0.1V	1μF<Cap<10μF: 0.2V		Cap≥10μF: 0.1V	0603	0805	Cap≤1μF: 1V	Cap<10μF: 1V	1μF<Cap≤4.7μF: 0.5V	Cap=10μF: 0.5V	Cap>4.7μF: 0.2V	Cap>10μF: 0.2V	1206	1210	Cap≤10μF: 1V	Cap≤10μF: 1V	10μF<Cap≤100μF: 0.5V	10μF<Cap≤100μF: 0.5V	Cap>100μF: 0.2V	Cap>100μF: 0.2V
T.C.	Capacitance Change																																															
NPO	±30 (ppm/°C)																																															
X7R	±15%																																															
X5R	±15%																																															
Y5V	+30%~-80%																																															
T.C.	Operating Temp																																															
NPO	-55 ~ 125°C at 25°C																																															
X7R	-55 ~ 125°C at 25°C																																															
X5R	-55 ~ 85°C at 25°C																																															
Y5V	-25 ~ 85°C at 20°C																																															
0201	0402																																															
Cap<0.1μF:1V	Cap<1μF: 1V																																															
0.1μF≤Cap<1μF: 0.2V	Cap=1μF: 0.5V																																															
Cap≥1μF: 0.1V	1μF<Cap<10μF: 0.2V																																															
	Cap≥10μF: 0.1V																																															
0603	0805																																															
Cap≤1μF: 1V	Cap<10μF: 1V																																															
1μF<Cap≤4.7μF: 0.5V	Cap=10μF: 0.5V																																															
Cap>4.7μF: 0.2V	Cap>10μF: 0.2V																																															
1206	1210																																															
Cap≤10μF: 1V	Cap≤10μF: 1V																																															
10μF<Cap≤100μF: 0.5V	10μF<Cap≤100μF: 0.5V																																															
Cap>100μF: 0.2V	Cap>100μF: 0.2V																																															
Adhesive Strength of Termination	No remarkable damage or removal of the terminations	Pressurizing force: 0201:2N 0402&0603:5N>0603:10N Test time: 10±1 sec																																														
Vibration Resistance	No remarkable damage Cap change and Q/D.F.: To meet initial spec	Vibration frequency: 10~55Hz/min Total amplitude: 1.5mm Test time: 6hrs.(two hrs each in three mutually Perpendicular directions.) *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Cap./DF(Q) Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.																																														
Solderability	95% min. coverage of all metalized area.	Solder temperature: 235±5°C Dipping time: 2±0.5 sec.																																														

Multilayer Ceramic Chip Capacitor

Item	Requirement	Test Method															
Bending Test	No remarkable damage. Cap change : NP0: within $\pm 5\%$ or 0.5pF whichever is larger X7R, X5R, X6S, X7S: within $\pm 12.5\%$ Y5V: within $\pm 30\%$ (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)	The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5 ± 1 sec. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp. Measurement to be made after keeping at room temp. for 24 ± 2 hrs.															
Resistance to Soldering Heat	No remarkable damage. Cap change: NP0: within $\pm 2.5\%$ or 0.25pF whichever is larger X7R, X5R, X6S, X7S: within $\pm 7.5\%$ Y5V: within $\pm 20\%$ Q/D.F., I.R. and dielectric strength: To meet initial requirements. 25% max. leaching on each edge	Solder temperature: $260 \pm 5^\circ\text{C}$ Dipping time: 10 ± 1 sec Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp. Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp															
Temperature Cycle	No remarkable damage. * Cap change : NP0: within $\pm 2.5\%$ or 0.25pF whichever is larger X7R, X5R, X6S, X7S: within $\pm 7.5\%$ Y5V: within $\pm 20\%$ * Q/D.F., I.R. and dielectric strength: To meet initial requirements	Conduct the five cycles according to the temperature and time. <table border="1"> <thead> <tr> <th>Step</th><th>Temp.($^\circ\text{C}$)</th><th>Time(min)</th></tr> </thead> <tbody> <tr> <td>1</td><td>Min. operating temp.+0/-3</td><td>30 ± 3</td></tr> <tr> <td>2</td><td>Room temp</td><td>2-3</td></tr> <tr> <td>3</td><td>Max. operating temp.+3/-0</td><td>30 ± 3</td></tr> <tr> <td>4</td><td>Room temp.</td><td>2-3</td></tr> </tbody> </table> Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp. Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp.	Step	Temp.($^\circ\text{C}$)	Time(min)	1	Min. operating temp.+0/-3	30 ± 3	2	Room temp	2-3	3	Max. operating temp.+3/-0	30 ± 3	4	Room temp.	2-3
Step	Temp.($^\circ\text{C}$)	Time(min)															
1	Min. operating temp.+0/-3	30 ± 3															
2	Room temp	2-3															
3	Max. operating temp.+3/-0	30 ± 3															
4	Room temp.	2-3															

Item	Requirement	Test Method																																																																																																		
Humidity (steady state)	No remarkable damage. Cap change: NP0: within $\pm 5\%$ or $0.5\mu\text{F}$ whichever is larger X7R, X5R: $\geq 10\text{V}^{**}$, within $\pm 12.5\%$; $\leq 6.3\text{V}$ within $\pm 25\%$; $C \geq 1\mu\text{F}$, within $\pm 25\%$ $**10\text{V}$: $0603 \geq 4.7\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0201 \geq 0.1\mu\text{F}$, within $\pm 25\%$; Y5V: $\geq 10\text{V}$, within $\pm 30\%$; $\leq 6.3\text{V}$, within $+30/-40\%$ Q/D.F. value: NP0: More than 30pF $Q \geq 350$, $10\text{pF} \leq C \leq 30\text{pF}$, $Q \geq 275 + 2.5C$ Less than 10pF $Q \geq 200 + 10C$ X7R, X5R: <table><tr><th>Rated vol.</th><th>D.F. $\leq$</th><th colspan="2">Exception of D.F. $\leq$</th></tr><tr><td rowspan="3">$\geq 100\text{V}$</td><td rowspan="3">3%</td><td>6%</td><td>$1206 \geq 0.47\mu\text{F}$</td></tr><tr><td>7.5%</td><td>$0603 \geq 0.068\mu\text{F}$; $0805 > 0.1\mu\text{F}$; $1206 > 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$</td></tr><tr><td>20%</td><td>$0805 > 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$</td></tr><tr><td rowspan="3">$\geq 50\text{V}$</td><td rowspan="3">3%</td><td>6%</td><td>$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$</td></tr><tr><td>10%</td><td>$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>20%</td><td>$0402 \geq 0.1\mu\text{F}$; $0603 > 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>35V</td><td>5%</td><td>20%</td><td>$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td rowspan="4">25V</td><td rowspan="4">5%</td><td>10%</td><td>$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>14%</td><td>$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$</td></tr><tr><td>15%</td><td>$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$ $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td>20%</td><td>$0402 \geq 0.47\mu\text{F}$</td></tr><tr><td rowspan="2">16V</td><td rowspan="2">5%</td><td>10%</td><td>$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>15%</td><td>$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td rowspan="2">10V</td><td rowspan="2">7.5%</td><td>15%</td><td>$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$) $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td>20%</td><td>$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$</td></tr><tr><td>6.3V</td><td>15%</td><td>30%</td><td>$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$ $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$</td></tr></table> Y5V: <table><tr><th>Rated vol.</th><th>D.F. $\leq$</th><th colspan="2">Exception of D.F. $\leq$</th></tr><tr><td rowspan="2">$\geq 50\text{V}$</td><td rowspan="2">7.5%</td><td>10%</td><td>$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$</td></tr><tr><td>20%</td><td>$1210 \geq 6.8\mu\text{F}$</td></tr><tr><td>35V</td><td>10%</td><td>—</td><td>—</td></tr><tr><td rowspan="2">25V</td><td rowspan="2">7.5%</td><td>10%</td><td>$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>15%</td><td>$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td rowspan="2">16V ($C < 1.0\mu\text{F}$)</td><td rowspan="2">10%</td><td>12.5%</td><td>$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$</td></tr><tr><td>20%</td><td>$0402 \geq 0.22\mu\text{F}$</td></tr><tr><td>16V ($C \geq 1.0\mu\text{F}$)</td><td>12.5%</td><td>20%</td><td>$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$</td></tr><tr><td>10V</td><td>20%</td><td>30%</td><td>$0402 \geq 0.47\mu\text{F}$</td></tr><tr><td>6.3V</td><td>30%</td><td>-</td><td>-</td></tr></table> I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, Y5V) <table><tr><th>Rated Voltage</th><th>Insulation Resistance</th></tr><tr><td>100V: X7R</td><td rowspan="7">10GΩ or RxC $\geq 10\Omega\text{-F}$ Whichever is smaller</td></tr><tr><td>50V: $0402 > 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$</td></tr><tr><td>10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$ $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$</td></tr><tr><td>6.3V</td></tr></table>	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		$\geq 100\text{V}$	3%	6%	$1206 \geq 0.47\mu\text{F}$	7.5%	$0603 \geq 0.068\mu\text{F}$; $0805 > 0.1\mu\text{F}$; $1206 > 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$	20%	$0805 > 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$	$\geq 50\text{V}$	3%	6%	$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$	10%	$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	20%	$0402 \geq 0.1\mu\text{F}$; $0603 > 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$	35V	5%	20%	$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$	25V	5%	10%	$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$	14%	$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$	15%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$ $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$	20%	$0402 \geq 0.47\mu\text{F}$	16V	5%	10%	$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	15%	$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$	10V	7.5%	15%	$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$) $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$	20%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$	6.3V	15%	30%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$ $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$	20%	$1210 \geq 6.8\mu\text{F}$	35V	10%	—	—	25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	15%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$	16V ($C < 1.0\mu\text{F}$)	10%	12.5%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$	20%	$0402 \geq 0.22\mu\text{F}$	16V ($C \geq 1.0\mu\text{F}$)	12.5%	20%	$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$	10V	20%	30%	$0402 \geq 0.47\mu\text{F}$	6.3V	30%	-	-	Rated Voltage	Insulation Resistance	100V: X7R	10G Ω or RxC $\geq 10\Omega\text{-F}$ Whichever is smaller	50V: $0402 > 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$	25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$	16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$	10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$ $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$	6.3V	Test temp.: $40 \pm 2^\circ\text{C}$ Humidity: 90~95%RH Test time: $500 \pm 24/-0\text{hrs}$. Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for $24 \pm 2\text{hrs}$ at room temp. Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for $24 \pm 2\text{hrs}$ at room temp.
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																																																																		
$\geq 100\text{V}$	3%	6%	$1206 \geq 0.47\mu\text{F}$																																																																																																	
		7.5%	$0603 \geq 0.068\mu\text{F}$; $0805 > 0.1\mu\text{F}$; $1206 > 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$																																																																																																	
		20%	$0805 > 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$																																																																																																	
$\geq 50\text{V}$	3%	6%	$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$																																																																																																	
		10%	$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																																																																	
		20%	$0402 \geq 0.1\mu\text{F}$; $0603 > 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																																																																	
35V	5%	20%	$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																																																																	
25V	5%	10%	$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																																																																	
		14%	$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$																																																																																																	
		15%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$ $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																																																																	
		20%	$0402 \geq 0.47\mu\text{F}$																																																																																																	
16V	5%	10%	$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																																																																	
		15%	$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																																																																	
10V	7.5%	15%	$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$) $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																																																																	
		20%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$																																																																																																	
6.3V	15%	30%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$ $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$																																																																																																	
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																																																																		
$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$																																																																																																	
		20%	$1210 \geq 6.8\mu\text{F}$																																																																																																	
35V	10%	—	—																																																																																																	
25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																																																																	
		15%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																																																																	
16V ($C < 1.0\mu\text{F}$)	10%	12.5%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$																																																																																																	
		20%	$0402 \geq 0.22\mu\text{F}$																																																																																																	
16V ($C \geq 1.0\mu\text{F}$)	12.5%	20%	$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$																																																																																																	
10V	20%	30%	$0402 \geq 0.47\mu\text{F}$																																																																																																	
6.3V	30%	-	-																																																																																																	
Rated Voltage	Insulation Resistance																																																																																																			
100V: X7R	10G Ω or RxC $\geq 10\Omega\text{-F}$ Whichever is smaller																																																																																																			
50V: $0402 > 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																																																																				
35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																																																																				
25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																																																																				
16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$																																																																																																				
10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$ $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$																																																																																																				
6.3V																																																																																																				

Item	Requirement	Test Method																																																		
Humidity load	No remarkable damage. Cap change: NP0: $\pm 7.5\%$ or $0.75\mu\text{F}$ whichever is larger. X7R, X5R, X6S, X7S: $\geq 10\text{V}^{**}$, within $\pm 12.5\%$; $\leq 6.3\text{V}$ within $\pm 25\%$; TT series & $C \geq 1\mu\text{F}$, within $\pm 25\%$ $**10\text{V}$: 0603 $4.7\mu\text{F}$; 0402 $1\mu\text{F}$; 0201 $\geq 0.1\mu\text{F}$, within $\pm 25\%$; Y5V: $\geq 10\text{V}$, within $\pm 30\%$; $\leq 6.3\text{V}$, within $+30/-40\%$ Q/D.F. value: NP0: $C \geq 30\mu\text{F}$, $Q \geq 200$; $C < 30\mu\text{F}$, $Q \geq 100 + 10/3C$ X7R, X5R:	Test temp. : $40 \pm 2^\circ\text{C}$ Humidity : 90~95%RH Test time : 500+24/-0 hrs. To apply voltage : Rated voltage (MAX. 500V) Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp. Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24 ± 2 hrs at room temp.																																																		
	<table><tr><td>Rated vol.</td><td>D.F. $\leq$</td><td colspan="2">Exception of D.F. $\leq$</td></tr><tr><td rowspan="3">$\geq 100\text{V}$</td><td rowspan="3">3%</td><td>6%</td><td>$1206 \geq 0.47\mu\text{F}$</td></tr><tr><td>7.5%</td><td>$0603 \geq 0.068\mu\text{F}$; $0805 > 0.1\mu\text{F}$; $1206 > 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$</td></tr><tr><td>20%</td><td>$0805 > 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$</td></tr><tr><td rowspan="3">$\geq 50\text{V}$</td><td rowspan="3">3%</td><td>6%</td><td>$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$</td></tr><tr><td>10%</td><td>$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>20%</td><td>$0402 \geq 0.1\mu\text{F}$; $0603 > 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>35V</td><td>5%</td><td>20%</td><td>$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td rowspan="4">25V</td><td rowspan="4">5%</td><td>10%</td><td>$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>14%</td><td>$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$</td></tr><tr><td>15%</td><td>$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td>20%</td><td>$0402 \geq 0.47\mu\text{F}$</td></tr><tr><td rowspan="2">16V</td><td rowspan="2">5%</td><td>10%</td><td>$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>15%</td><td>$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td rowspan="2">10V</td><td rowspan="2">7.5%</td><td>15%</td><td>$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$); $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td>20%</td><td>$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$</td></tr><tr><td>6.3V</td><td>15%</td><td>30%</td><td>$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$; $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$</td></tr></table>	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		$\geq 100\text{V}$	3%	6%	$1206 \geq 0.47\mu\text{F}$	7.5%	$0603 \geq 0.068\mu\text{F}$; $0805 > 0.1\mu\text{F}$; $1206 > 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$	20%	$0805 > 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$	$\geq 50\text{V}$	3%	6%	$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$	10%	$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	20%	$0402 \geq 0.1\mu\text{F}$; $0603 > 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$	35V	5%	20%	$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$	25V	5%	10%	$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$	14%	$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$	15%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$	20%	$0402 \geq 0.47\mu\text{F}$	16V	5%	10%	$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	15%	$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$	10V	7.5%	15%	$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$); $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$	20%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$	6.3V	15%	30%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$; $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$	
	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																	
	$\geq 100\text{V}$	3%	6%	$1206 \geq 0.47\mu\text{F}$																																																
			7.5%	$0603 \geq 0.068\mu\text{F}$; $0805 > 0.1\mu\text{F}$; $1206 > 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$																																																
			20%	$0805 > 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$																																																
	$\geq 50\text{V}$	3%	6%	$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$																																																
			10%	$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																
			20%	$0402 \geq 0.1\mu\text{F}$; $0603 > 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																
	35V	5%	20%	$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																
	25V	5%	10%	$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																
			14%	$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$																																																
			15%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																
			20%	$0402 \geq 0.47\mu\text{F}$																																																
	16V	5%	10%	$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																
15%			$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																	
10V	7.5%	15%	$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$); $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																	
		20%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$																																																	
6.3V	15%	30%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$; $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$																																																	
Y5V:	<table><tr><td>Rated vol.</td><td>D.F. $\leq$</td><td colspan="2">Exception of D.F. $\leq$</td></tr><tr><td rowspan="2">$\geq 50\text{V}$</td><td rowspan="2">7.5%</td><td>10%</td><td>$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$</td></tr><tr><td>20%</td><td>$1210 \geq 6.8\mu\text{F}$</td></tr><tr><td>35V</td><td>10%</td><td>—</td><td>—</td></tr><tr><td rowspan="2">25V</td><td rowspan="2">7.5%</td><td>10%</td><td>$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>15%</td><td>$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$</td></tr><tr><td rowspan="2">16V ($C < 1.0\mu\text{F}$)</td><td rowspan="2">10%</td><td>12.5%</td><td>$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$</td></tr><tr><td>20%</td><td>$0402 \geq 0.22\mu\text{F}$</td></tr><tr><td>16V ($C \geq 1.0\mu\text{F}$)</td><td>12.5%</td><td>20%</td><td>$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$</td></tr><tr><td>10V</td><td>20%</td><td>30%</td><td>$0402 \geq 0.47\mu\text{F}$</td></tr><tr><td>6.3V</td><td>30%</td><td>-</td><td>-</td></tr></table>	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$	20%	$1210 \geq 6.8\mu\text{F}$	35V	10%	—	—	25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	15%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$	16V ($C < 1.0\mu\text{F}$)	10%	12.5%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$	20%	$0402 \geq 0.22\mu\text{F}$	16V ($C \geq 1.0\mu\text{F}$)	12.5%	20%	$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$	10V	20%	30%	$0402 \geq 0.47\mu\text{F}$	6.3V	30%	-	-													
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																		
$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$																																																	
		20%	$1210 \geq 6.8\mu\text{F}$																																																	
35V	10%	—	—																																																	
25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																	
		15%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$																																																	
16V ($C < 1.0\mu\text{F}$)	10%	12.5%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$																																																	
		20%	$0402 \geq 0.22\mu\text{F}$																																																	
16V ($C \geq 1.0\mu\text{F}$)	12.5%	20%	$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$																																																	
10V	20%	30%	$0402 \geq 0.47\mu\text{F}$																																																	
6.3V	30%	-	-																																																	
I.R.: $\geq 10\text{V}$, 500M Ω or 25 $\Omega \cdot \text{F}$ whichever is smaller. Class II (X7R, X5R, Y5V)	<table><tr><th>Rated Voltage</th><th>Insulation Resistance</th></tr><tr><td>100V: X7R</td><td rowspan="7">500MΩ or RxC $\geq 5\Omega \cdot \text{F}$ Whichever is smaller</td></tr><tr><td>50V: $0402 > 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$</td></tr><tr><td>35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$</td></tr><tr><td>16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$</td></tr><tr><td>10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$</td></tr><tr><td>6.3V</td></tr></table>	Rated Voltage	Insulation Resistance	100V: X7R	500M Ω or RxC $\geq 5\Omega \cdot \text{F}$ Whichever is smaller	50V: $0402 > 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$	35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$	25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$	16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$	10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$	6.3V																																									
Rated Voltage	Insulation Resistance																																																			
100V: X7R	500M Ω or RxC $\geq 5\Omega \cdot \text{F}$ Whichever is smaller																																																			
50V: $0402 > 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$																																																				
35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																				
25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$																																																				
16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$																																																				
10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$																																																				
6.3V																																																				

Item	Requirement			Test Method		
High Temperature Load (Endurance)	No remarkable damage. Cap change: NP0: $\pm 3.0\%$ or $\pm 0.3\text{pF}$ whichever is larger X7R, X5R, X6S, X7S: $\geq 10\text{V}^{**}$, within $\pm 12.5\%$; $\leq 6.3\text{V}$ within $\pm 25\%$; TT series & C $\geq 1\mu\text{F}$, within $\pm 25\%$ $**10\text{V}$: $0603 \geq 4.7\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0201 \geq 0.1\mu\text{F}$, within $\pm 25\%$; Y5V: $\geq 10\text{V}$, within $\pm 30\%$; $\leq 6.3\text{V}$, within $+30/-40\%$ Q/D.F. value: NP0: More than 30pF , $Q \geq 350$ $10\text{pF} \leq C < 30\text{pF}$, $Q \geq 275 + 2.5C$ Less than 10pF , $Q \geq 200 + 10C$ X7R, X5R:					
	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$			
	$\geq 100\text{V}$	3%	6%	$1206 \geq 0.47\mu\text{F}$		
			7.5%	$0603 \geq 0.068\mu\text{F}$; $0805 \geq 0.1\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 2.2\mu\text{F}$		
			20%	$0805 \geq 0.22\mu\text{F}$; $1210 \geq 3.3\mu\text{F}$		
	$\geq 50\text{V}$	3%	6%	$0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$		
			10%	$0201 \geq 0.01\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$		
			20%	$0402 \geq 0.1\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$		
	35V	5%	20%	$0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$		
	25V	5%	10%	$0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$		
			14%	$0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$		
			15%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$		
			20%	$0402 \geq 0.47\mu\text{F}$		
	16V	5%	10%	$0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$		
			15%	$0201 \geq 0.01\mu\text{F}$ ($0201/\text{X7R} \geq 0.022\mu\text{F}$); $0402 \geq 0.33\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$		
	10V	7.5%	15%	$0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/\text{X7R} \geq 0.22\mu\text{F}$); $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$		
			20%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$		
	6.3V	15%	30%	$0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$; $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$		
Y5V:						
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$				
$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$			
		20%	$1210 \geq 6.8\mu\text{F}$			
35V	10%	—	—			
25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$			
		15%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$			
16V (C < 1.0 μF)	10%	12.5%	$0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$			
		20%	$0402 \geq 0.22\mu\text{F}$			
16V (C $\geq 1.0\mu\text{F}$)	12.5%	20%	$0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$			
10V	20%	30%	$0402 \geq 0.47\mu\text{F}$			
6.3V	30%	-	-			
I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, Y5V)						
Rated Voltage			Insulation Resistance			
100V: X7R			500M Ω or RxC $\geq 5\Omega\text{-F}$ Whichever is smaller			
50V: $0402 \geq 0.01\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$						
35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$						
25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$						
16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$						
10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$						
6.3V						
Test temp. : NP0, X7R: $125 \pm 3^\circ\text{C}$ X5R, Y5V: $85 \pm 3^\circ\text{C}$ To apply voltage: (1) $\leq 6.3\text{V}$ or C $\geq 10\mu\text{F}$: 150% of rated voltage. (2) $10\text{V} \leq U_r < 500\text{V}$: 200% of rated voltage. (3) 500V : 150% of rated voltage. (4) $U_r \geq 630\text{V}$: 120% of rated voltage. (5) 100% of rated voltage for below range.						
Size	Dielectric	Rated voltage	Capacitance range			
0201	X5R, X7R	$\leq 10\text{V}$	$C \geq 0.1\mu\text{F}$			
		$\geq 16\text{V}$	$C > 0.1\mu\text{F}$			
0402	X5R, X7R, Y5V	6.3V, 10V, 16V, 25V	$C \geq 1.0\mu\text{F}$			
0603	X5R, X7R	6.3V, 10V, 25V, 35V	$C \geq 4.7\mu\text{F}$			
			$C \geq 1.0\mu\text{F}$			
0805	X5R, X7R	6.3V	$C \geq 22\mu\text{F}$			
		10V~50V	$C \geq 10\mu\text{F}$			
1206	X5R, X7R NPO	6.3V	$C \geq 47\mu\text{F}$			
		3000V	$C \geq 1.5\text{pF}$			
1210	X5R, X7R X7R	16V	$C \geq 47\mu\text{F}$			
		100V	$C \geq 3.3\mu\text{F}$			
(6) 150% of rated voltage for below range						
Size	Dielectric	Rated voltage	Capacitance range			
0201	X5R, X7R X7R	16V, 25V	$C \geq 0.1\mu\text{F}$			
		16V	$C > 0.022\mu\text{F}$			
0402	X5R, X7R, Y5V	50V	$C \geq 1.0\mu\text{F}$			
		10~25V	$C \geq 0.022\mu\text{F}$			
	Y5V	16V	$C \geq 0.47\mu\text{F}$			
			$C \geq 0.1\mu\text{F}$			
0603	X5R, X7R, Y5V	50V	$C \geq 1.0\mu\text{F}$			
		10V, 16V, 50V	$C \geq 1.0\mu\text{F}$			
	Y5V	16V	$C \geq 2.2\mu\text{F}$			
			$C \geq 2.2\mu\text{F}$			
0805	X5R, X7R	10V~50V	$C \geq 4.7\mu\text{F}$			
		50V	$C \geq 2.2\mu\text{F}$			
		100V	$C \geq 0.47\mu\text{F}$			
	Y5V	16V	$C \geq 4.7\mu\text{F}$			
1206	X5R, X7R	100V	$C \geq 1.0\mu\text{F}$			
1210	X5R, X7R	50V~100V	$C \geq 2.2\mu\text{F}$			


■ Packaging

Packaging Quantity

Unit: mm

Type	Thickness / Symbol		Packaging (7" Reel)	
			Paper tape	Plastic tape
0201	0.30±0.03	L	15K	-
	0.30±0.05	L	15K	-
	0.30±0.09	L	15K	-
0402	0.50±0.05	N	10K	-
	0.5+0.02/-0.05	Q	10K	-
	0.50±0.20	E	10K	-
0603	0.50±0.10	H	4K	-
	0.80±0.10	S	4K	-
	0.80 +0.15 / -0.10	X	4K	-
0805	0.50±0.10	H	4K	-
	0.60±0.10	A	4K	-
	0.80±0.10	B	4K	-
	0.85±0.10	T	4K	-
	1.25±0.10	D	-	3K
	1.25±0.20	I	-	3K
1206	0.80±0.10	B	4K	-
	0.85±0.10	T	4K	-
	0.95±0.10	C	-	3K
	1.15±0.15	J	-	3K
	1.25±0.10	D	-	3K
	1.60±0.20	G	-	2K
	1.60 +0.30 / -0.10	P	-	2K
1210	0.85±0.10	T	-	3K
	0.95±0.10	C	-	3K
	1.25±0.10	D	-	3K
	1.60±0.20	G	-	2K
	2.00±0.20	K	-	1K
	2.50±0.30	M	-	1K 0.5K
1808	1.25±0.10	D	-	2K
	1.10±0.15	F	-	2K
	1.60±0.20	G	-	2K
	2.00±0.20	K	-	1K
1812	1.25±0.10	D	-	1K
	1.60±0.20	G	-	1K
	2.00±0.20	K	-	1K
	2.50±0.30	M	-	0.5K
	2.80±0.30	U	-	0.5K
0612	0.80±0.10	B	4K	-


Tape and Reel



Unit: mm

Type	Chip Size							
	0201	0402	0603	0805	1206/0612	1210	1808	1812
ΦC	13.0±1.0	13.0±1.0	13.0±1.0	13.0±1.0	13.0±1.0	13.0±1.0	13.0±1.0	13.0±1.0
W	9.0±1.0	9.0±1.0	9.0±1.0	9.0±1.0	9.0±1.0	9.0±1.0	13.5±1.0	13.5±1.0
ΦA	178±1.0(7")	178±1.0(7")	178±1.0(7")	178±1.0(7")	178±1.0(7")	178±1.0(7")	178±1.0(7")	178±1.0(7")
ΦB	60.5±1.0(7")	60.5±1.0(7")	60.5±1.0(7")	60.5±1.0(7")	60.5±1.0(7")	60.5±1.0(7")	80.0±1.0(7")	80.0±1.0(7")


Plastic Tape Size Specification



Unit: mm

Type	0805		1206					1210						1808				1812					
Thickness	D	I	C	J	D	G	P	T	C	D	G	K	M	D	F	G	K	D	F	G	K	M	U
A ₀	<1.80		<200			<2.30		<3.05			<3.05		<3.20		<2.50			<3.90					
B ₀	<2.70		<3.70			<4.00		<3.80			<3.80		<3.95		<5.30			<5.30					
T	0.23±0.10		0.23±0.10			0.23±0.10		0.23±0.10			0.23±0.10		0.23±0.10		0.25±0.10			0.25±0.10					
K ₀	<2.50		<2.50			<2.50		<1.50			<2.50		<3.00		<2.50			<2.50					<3.50
W	8.00±0.20		8.00±0.20			8.00±0.20		8.00±0.20			8.00±0.20		8.00±0.20		12.0±0.20			12.0±0.20					
P ₀	4.00±0.10		4.00±0.10			4.00±0.10		4.00±0.10			4.00±0.10		4.00±0.10		4.00±0.10			4.00±0.10					
P ₁	4.00±0.10		4.00±0.10			4.00±0.10		4.00±0.10			4.00±0.10		4.00±0.10		4.00±0.10			8.00±0.10					
P ₂	2.00±0.05		2.00±0.05			2.00±0.05		2.00±0.05			2.00±0.05		2.00±0.05		2.00±0.10			2.00±0.05					
D ₀	1.50+0.1/-0		1.50±0.05			1.50+0.1/-0		1.50+0.1/-0			1.50+0.1/-0		1.50+0.1/-0		1.50+0.1/-0			1.50+0.1/-0					
D ₁	1.00±0.10		1.00±0.10			1.00±0.10		1.00±0.10			1.00±0.10		1.00±0.10		1.50±0.10			1.50±0.10					
E	1.75±0.10		1.75±0.10			1.75±0.10		1.75±0.10			1.75±0.10		1.75±0.10		1.75±0.10			1.75±0.10					
F	3.50±0.05		3.50±0.05			3.50±0.05		3.50±0.05			3.50±0.05		3.50±0.05		5.50±0.10			5.50±0.10					

Paper Tape Size Specification



Unit: mm

Type	0201	0402		0603			0805				1206/0612	
Thickness	L	N	E	S	H	X	A	H	B	T	B	T
A ₀	0.39±0.07	0.70±0.20		1.05±0.30			1.50±0.20		1.50±0.20		1.90±0.50	
B ₀	0.69±0.07	1.20±0.20		1.80±0.30			2.30±0.20		2.30±0.20		3.50±0.50	
T	≤ 0.50	≤ 0.80		≤ 1.20			≤ 1.15		≤ 1.30		≤ 1.30	
W	8.00±0.10	8.00±0.10		8.00±0.10			8.00±0.10		8.00±0.10		8.00±0.10	
P ₀	4.00±0.10	4.00±0.10		4.00±0.10			4.00±0.10		4.00±0.10		4.00±0.10	
P ₁	2.00±0.05	2.00±0.05		4.00±0.10			4.00±0.10		4.00±0.10		4.00±0.10	
P ₂	2.00±0.05	2.00±0.05		2.00±0.05			2.00±0.05		2.00±0.05		2.00±0.05	
D ₀	1.55±0.05	1.55±0.05		1.55±0.05			1.55±0.05		1.55±0.05		1.50±0.05	
E	1.75±0.05	1.75±0.05		1.75±0.05			1.75±0.05		1.75±0.05		1.75±0.10	
F	3.50±0.05	3.50±0.05		3.50±0.05			3.50±0.05		3.50±0.05		3.50±0.05	