

APPROVAL SHEET

MULTILAYER CERAMIC CAPACITORS

High Capacitance Series

0402 to 1812 Sizes

X7R, X5R & Y5V Dielectrics

RoHS Compliance

*Contents in this sheet are subject to change without prior notice.

1. DESCRIPTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

WTC high capacitance MLCC offers low ESR and excellent frequency characteristics to be suited for coupling and decoupling applications in circuit. The high dielectric constant material X7R, X5R and Y5V are used for this series product.

2. FEATURES

- a. Small size with high capacitance.
- b. Capacitor with lead-free termination (pure Tin).

3. APPLICATIONS

- a. Digital circuit coupling or decoupling applications.
- b. For high frequency and high-density type power suppliers.
- c. For bypassing.


4. HOW TO ORDER

1206	E	106	Z	100	C	I
<u>Size</u>	<u>Dielectric</u>	<u>Capacitance</u>	<u>Tolerance</u>	<u>Rated voltage</u>	<u>Termination</u>	<u>Packaging</u>
Inch (mm)						
0402 (1005)	B=X7R	Two significant digits followed by no. of zeros.	K=±10%	Two significant digits followed by no. of zeros.	C=Cu/Ni/Sn	T=7" reeled
0603 (1608)	X=X5R		M=±20%			G=13" reeled
0805 (2012)	F=Y5V	And R is in place of decimal point.	Z=-20/+80%	And R is in place of decimal point.		
1206 (3216)						
1210 (3225)		eg.: $106=10 \times 10^6$ $=10\mu F$		6R3=6.3 VDC 100=10 VDC 160=16 VDC 250=25 VDC 500=50 VDC 101=100 VDC		
1812 (4532)						

5. EXTERNAL DIMENSIONS

Size Inch (mm)	L (mm)	W (mm)	T (mm)/Symbol	Remark	M _B (mm)
0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N	# 0.25 +0.05/-0.10
0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S	0.40±0.15
0805 (2012)	1.60±0.15/-0.10	0.80±0.15/-0.10	0.80±0.15/-0.10	X	0.50±0.20
	2.00±0.15	1.25±0.10	0.80±0.10	B	
	2.00±0.20	1.25±0.20	1.25±0.20	D # I	
1206 (3216)	3.20±0.15	1.60±0.15	0.95±0.10	C #	0.60±0.20
			1.25±0.10	D #	
	3.20±0.20	1.60±0.20	1.60±0.20	G #	
			1.15±0.15	J #	
	3.20±0.30/-0.10	1.60±0.30/-0.10	1.60±0.30/-0.10	P #	
1210 (3225)	3.20±0.30	2.50±0.20	0.95±0.10	C #	0.75±0.25
			1.25±0.10	D #	
	3.20±0.40	2.50±0.30	1.60±0.20	G #	
			2.00±0.20	K #	
			2.50±0.30	M #	
1812 (4532)	4.50±0.40	3.20±0.30	1.25±0.10	D #	0.75±0.25
			2.00±0.20	K #	
	4.50±0.40	3.20±0.40	2.50±0.30	M #	

Reflow soldering only is recommended.



6. GENERAL ELECTRICAL DATA

Dielectric	X7R	X5R	Y5V
Size	0402, 0603, 0805, 1206, 1210, 1812		
Capacitance range*	0.56µF to 10µF		0.027µF to 22µF
Capacitance tolerance**	K ($\pm 10\%$), M ($\pm 20\%$)		Z (-20/+80%)
Rated voltage (WVDC)	6.3V, 10V, 16V, 25V, 50V, 100V		
Tan δ*	Note 1		
Insulation resistance at Ur	RxC≥500ΩxF		
Operating temperature	-55 to +125°C	-55 to +85°C	-25 to +85°C
Capacitance characteristic	±15%		
Termination	Ni/Sn (lead-free termination)		

* Measured at 1.0±0.2Vrms, 1.0kHz±10% for C≤10µF; 0.5±0.2Vrms, 120Hz±20% for C>10µF, 30~70% related humidity, 25°C ambient temperature for X7R, X5R and at 20°C for Y5V.

** Preconditioning for Class II MLCC: Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement.

Note 1:

X7R/X5R

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥50V	2.5%	3% 0603≥0.047µF; 0805≥0.18µF; 1206≥0.47µF
25V	3.5%	5% 0805≥1µF; 1210≥10µF
		7% 0603≥0.33µF; 1206≥4.7µF
		10% 0402≥0.10µF; 0603≥0.47µF; 0805≥2.2µF; 1206≥6.8µF
16V	3.5%	5% 0402≥0.033µF; 0603≥0.15µF; 0805≥0.68µF; 1206≥2.2µF; 1210≥4.7µF
		10% 0603≥0.68µF; 0805≥2.2µF; 1206≥4.7µF; 1210≥22µF
10V	5%	10% 0402≥0.33µF; 0603≥0.33µF; 0805≥2.2µF; 1206≥2.2µF; 1210≥22µF;
		15% 0201≥0.1µF; 0402≥1µF
6.3V	10%	15% 0603≥10µF; 0805≥4.7µF; 1206≥47µF; 1210≥100µF;
		20% 0402≥2.2µF

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥50V	5%	7% 0603≥0.1µF; 0805≥0.47µF; 1206≥4.7µF
35V	7%	---
25V	5%	7% 0402≥0.047µF; 0603≥0.1µF; 0805≥0.33µF; 1206≥1µF; 1210≥4.7µF
		9% 0402≥0.068µF; 0603≥0.47µF; 1206≥4.7µF; 1210≥22µF
16V (C<1.0µF)	7%	9% 0402≥0.068µF; 0603≥0.68µF
		12.5% 0402≥0.22µF
16V (C≥1.0µF)	9%	12.5% 0603≥2.2µF; 0805≥3.3µF; 1206≥10µF; 1210≥22µF; 1812≥47µF
10V	12.5%	20% 0402≥0.47µF
6.3V	20%	---

7. CAPACITANCE RANGE

7-1 X7R Dielectric

DIELECTRIC		X7R																					
SIZE		0603				0805				1206				1210					1812				
RATED VOLTAGE		6.3	10	16	6.3	10	16	25	6.3	10	16	25	50	10	16	25	50	100	10	16	25	50	100
Capacitance	0.56μF (564)		X	X																			
	0.68μF (684)		X	X																			
	0.82μF (824)		X	X																			
	1.0μF (105)	X	X	X		D	D	D		J	J	J	P	D	D	D	D	K	D	D	D	K	K
	1.5μF (155)				I				J	J	J	P											K
	2.2μF (225)			I	I	I	I	J	J	J	P			K	G							M	
	3.3μF (335)								P	P	P				G								
	4.7μF (475)		I	I		P	P	P	P		K	K	K										
	6.8μF (685)				P	P	P			K	K	K											
	10μF (106)		I											M	M	M							

1. The letter in cell is expressed the symbol of product thickness.

7-2 X5R Dielectric

Dielectric		X5R																				
Size		0402				0603				0805				1206				1210				1812
Rated Voltage (VDC)		6.3	10	16	25	6.3	10	16	25	6.3	10	16	25	6.3	10	16	25	6.3	10	16	25	6.3
Capacitance	0.027μF (273)			N																		
	0.033μF (333)			N																		
	0.039μF (393)			N																		
	0.047μF (473)			N																		
	0.056μF (563)		N	N																		
	0.068μF (683)		N	N																		
	0.082μF (823)	N	N	N																		
	0.10μF (104)	N	N	N	N																	
	0.15μF (154)																					
	0.22μF (224)	N	N	N						X	X											
	0.27μF (274)								X	X												
	0.33μF (334)	N	N			X	X	X	X													
	0.39μF (394)					X	X			X	X											
	0.47μF (474)	N	N					X	X	X												
	0.68μF (684)	N	N					X	X	X												
	0.82μF (824)					X	X	X														
	1.0μF (105)	N	N			X	X	X	X													
	1.5μF (155)					X				I	I				J	J			K	K		
	2.2μF (225)	N				X	X	X		I	I	I	I		J	J	P		K	K		
	3.3μF (335)								I	I	I	I	I		P	P	P					
	4.7μF (475)	N				X	X			I	I	I	I		P	P	P	P	K	K	K	
	6.8μF (685)													P	P							
	10μF (106)					X				I	I	I			P	P	P	P	K	K	K	
	22μF (226)								I	I				P	P			M	M	M		
	47μF (476)								I					P				M	M	M		
	100μF (107)																	M			U	

1. The letter in cell is expressed the symbol of product thickness.

7-3 Y5V Dielectric

DIELECTRIC		Y5V										
SIZE		0402		0603				0805				
RATED VOLTAGE (VDC)		63	10	63	10	16	25	6.3	10	16	25	50
Capacitance	1.0μF (105)	N	N		S	X	X		B	B	D	D
	1.5μF (155)				S				D	D		
	2.2μF (225)			S	S	X			D	D	I	I
	3.3μF (335)								D	D		
	4.7μF (475)			X	X				D	D	I	
	6.8μF (685)								I			
	10μF (106)							I	I	I		
	22μF (226)							I				

DIELECTRIC		Y5V																
SIZE		1206					1210					1812						
RATED VOLTAGE (VDC)		10	16	25	35	50	6.3	10	16	25	35	50	63	10	16	25	50	100
Capacitance	1.0μF (105)	C	C	C		C		C	C	C		C		D	D	D	D	D
	1.5μF (155)	C	C	C				C	C	C				D	D	D	D	D
	2.2μF (225)	C	C	C	J		C	C	C		G		D	D	D	D	D	
	3.3μF (335)	J	J	J			C	C	C				D	D	D	D	D	
	4.7μF (475)	J	J	J	J	P	C	C	D		G		D	D	D	D	D	
	6.8μF (685)	J	J				C	C	D				D	D	D	D	D	
	10μF (106)	J	J	P			D	D	G	K	G		D	D	D	K		
	22μF (226)	P	P				K	K	K						M			
	47μF (476)		P				K	K										
	100μF (107)					M												

1. The letter in cell is expressed the symbol of product thickness.





8. PACKAGING STYLE AND QUANTITY

Size	Thickness (mm)/Symbol	Paper tape				Plastic tape			
		7" reel	13" reel	7" reel	13" reel				
0402 (1005)	0.50±0.05	N	10k	50k		-		-	
0603 (1608)	0.80±0.07	S	4k	15k		-		-	
	0.80+0.15/-0.10	X	4k	15k		-		-	
0805 (2012)	0.80±0.10	B	4k	15k		-		-	
	1.25±0.10	D	-	-		3k		10k	
	1.25±0.20	I	-	-		3k		10k	
1206 (3216)	0.95±0.10	C	-	-		3k		10k	
	1.15±0.15	J	-	-		3K		10K	
	1.25±0.10	D	-	-		3k		10k	
	1.60±0.20	G	-	-		2k		-	
	1.60+0.30/-0.10	P	-	-		2k		-	
1210 (3225)	0.95±0.10	C	-	-		3k		10k	
	1.25±0.10	D	-	-		3k		10k	
	1.60±0.20	G	-	-		2k		-	
	2.00±0.20	K	-	-		1k		-	
	2.50±0.30	M	-	-		1k		-	
1812 (4532)	1.25±0.10	D	-	-		1k		-	
	2.00±0.20	K	-	-		1k		-	
	2.50±0.30	M	-	-		0.5k			

Unit: pieces

9. ELECTRICAL CHARACTERISTICS

Typical Impedance/ESR vs. Frequency



10. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																																																																																												
1.	Visual and Mechanical	--	<ul style="list-style-type: none"> * No remarkable defect. * Dimensions to conform to individual specification sheet. 																																																																																												
2.	Capacitance	Class I:NP0	<ul style="list-style-type: none"> * Shall not exceed the limits given in the detailed spec. 																																																																																												
3.	Q/D.F. (Dissipation Factor)	Cap \leq 1000pF 1.0 \pm 0.2Vrms, 1MHz \pm 10% Cap>1000pF 1.0 \pm 0.2Vrms, 1KHz \pm 10% Class II:X7R, X5R, Y5V Cap \leq 10 μ F, 1.0 \pm 0.2Vrms, 1kHz \pm 10% Cap>10 μ F, 0.5 \pm 0.2Vrms, 120Hz \pm 20%	<ul style="list-style-type: none"> NP0: Cap\geq30pF, Q\geq1000; Cap<30pF, Q\geq400+20C X7R, X5R: <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th colspan="2">Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>\geq 50V</td> <td>2.5%</td> <td>3%</td> <td>0603\geq 0.047μF; 0805\geq 0.18μF; 1206\geq 0.47μF</td> </tr> <tr> <td></td> <td>5%</td> <td>5%</td> <td>0805\geq 1μF; 1210\geq 10μF</td> </tr> <tr> <td></td> <td>7%</td> <td>7%</td> <td>0603\geq 0.33μF; 1206\geq 4.7μF</td> </tr> <tr> <td></td> <td>10%</td> <td>10%</td> <td>0402\geq 0.10μF; 0603\geq 0.47μF; 0805\geq 2.2μF; 1206\geq 6.8μF</td> </tr> <tr> <td>25V</td> <td>3.5%</td> <td>5%</td> <td>0402\geq 0.033μF; 0603\geq 0.15μF; 0805\geq 0.68μF; 1206\geq 2.2μF; 1210\geq 4.7μF</td> </tr> <tr> <td></td> <td>10%</td> <td>10%</td> <td>0603\geq 0.68μF; 0805\geq 2.2μF; 1206\geq 4.7μF; 1210\geq 22μF</td> </tr> <tr> <td>16V</td> <td>3.5%</td> <td>5%</td> <td>0402\geq 0.33μF; 0603\geq 0.33μF; 0805\geq 2.2μF; 1206\geq 2.2μF; 1210\geq 22μF</td> </tr> <tr> <td></td> <td>10%</td> <td>10%</td> <td>0201\geq 0.1μF; 0402\geq 1μF</td> </tr> <tr> <td>10V</td> <td>5%</td> <td>10%</td> <td>0603\geq 10μF; 0805\geq 4.7μF; 1206\geq 47μF; 1210\geq 100μF;</td> </tr> <tr> <td></td> <td>15%</td> <td>15%</td> <td>0402\geq 2.2μF</td> </tr> <tr> <td>6.3V</td> <td>10%</td> <td>10%</td> <td>0402\geq 0.47μF</td> </tr> <tr> <td></td> <td>20%</td> <td>20%</td> <td>---</td> </tr> </tbody> </table> <ul style="list-style-type: none"> Y5V: <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th colspan="2">Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>\geq 50V</td> <td>5%</td> <td>7%</td> <td>0603\geq 0.1μF; 0805\geq 0.47μF; 1206\geq 4.7μF</td> </tr> <tr> <td>35V</td> <td>7%</td> <td>---</td> <td>---</td> </tr> <tr> <td>25V</td> <td>5%</td> <td>7%</td> <td>0402\geq 0.047μF; 0603\geq 0.1μF; 0805\geq 0.33μF; 1206\geq 1μF; 1210\geq 4.7μF</td> </tr> <tr> <td></td> <td>9%</td> <td>9%</td> <td>0402\geq 0.068μF; 0603\geq 0.47μF; 1206\geq 4.7μF; 1210\geq 22μF</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>7%</td> <td>9%</td> <td>0402\geq 0.068μF; 0603\geq 0.68μF</td> </tr> <tr> <td></td> <td>12.5%</td> <td>12.5%</td> <td>0402\geq 0.22μF</td> </tr> <tr> <td>16V (C\geq 1.0μF)</td> <td>9%</td> <td>12.5%</td> <td>0603\geq 2.2μF; 0805\geq 3.3μF; 1206\geq 10μF; 1210\geq 22μF; 1812\geq 47μF</td> </tr> <tr> <td>10V</td> <td>12.5%</td> <td>20%</td> <td>0402\geq 0.47μF</td> </tr> <tr> <td>6.3V</td> <td>20%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F. \leq	Exception of D.F. \leq		\geq 50V	2.5%	3%	0603 \geq 0.047 μ F; 0805 \geq 0.18 μ F; 1206 \geq 0.47 μ F		5%	5%	0805 \geq 1 μ F; 1210 \geq 10 μ F		7%	7%	0603 \geq 0.33 μ F; 1206 \geq 4.7 μ F		10%	10%	0402 \geq 0.10 μ F; 0603 \geq 0.47 μ F; 0805 \geq 2.2 μ F; 1206 \geq 6.8 μ F	25V	3.5%	5%	0402 \geq 0.033 μ F; 0603 \geq 0.15 μ F; 0805 \geq 0.68 μ F; 1206 \geq 2.2 μ F; 1210 \geq 4.7 μ F		10%	10%	0603 \geq 0.68 μ F; 0805 \geq 2.2 μ F; 1206 \geq 4.7 μ F; 1210 \geq 22 μ F	16V	3.5%	5%	0402 \geq 0.33 μ F; 0603 \geq 0.33 μ F; 0805 \geq 2.2 μ F; 1206 \geq 2.2 μ F; 1210 \geq 22 μ F		10%	10%	0201 \geq 0.1 μ F; 0402 \geq 1 μ F	10V	5%	10%	0603 \geq 10 μ F; 0805 \geq 4.7 μ F; 1206 \geq 47 μ F; 1210 \geq 100 μ F;		15%	15%	0402 \geq 2.2 μ F	6.3V	10%	10%	0402 \geq 0.47 μ F		20%	20%	---	Rated vol.	D.F. \leq	Exception of D.F. \leq		\geq 50V	5%	7%	0603 \geq 0.1 μ F; 0805 \geq 0.47 μ F; 1206 \geq 4.7 μ F	35V	7%	---	---	25V	5%	7%	0402 \geq 0.047 μ F; 0603 \geq 0.1 μ F; 0805 \geq 0.33 μ F; 1206 \geq 1 μ F; 1210 \geq 4.7 μ F		9%	9%	0402 \geq 0.068 μ F; 0603 \geq 0.47 μ F; 1206 \geq 4.7 μ F; 1210 \geq 22 μ F	16V (C<1.0 μ F)	7%	9%	0402 \geq 0.068 μ F; 0603 \geq 0.68 μ F		12.5%	12.5%	0402 \geq 0.22 μ F	16V (C \geq 1.0 μ F)	9%	12.5%	0603 \geq 2.2 μ F; 0805 \geq 3.3 μ F; 1206 \geq 10 μ F; 1210 \geq 22 μ F; 1812 \geq 47 μ F	10V	12.5%	20%	0402 \geq 0.47 μ F	6.3V	20%	---	---
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																																																													
\geq 50V	2.5%	3%	0603 \geq 0.047 μ F; 0805 \geq 0.18 μ F; 1206 \geq 0.47 μ F																																																																																												
	5%	5%	0805 \geq 1 μ F; 1210 \geq 10 μ F																																																																																												
	7%	7%	0603 \geq 0.33 μ F; 1206 \geq 4.7 μ F																																																																																												
	10%	10%	0402 \geq 0.10 μ F; 0603 \geq 0.47 μ F; 0805 \geq 2.2 μ F; 1206 \geq 6.8 μ F																																																																																												
25V	3.5%	5%	0402 \geq 0.033 μ F; 0603 \geq 0.15 μ F; 0805 \geq 0.68 μ F; 1206 \geq 2.2 μ F; 1210 \geq 4.7 μ F																																																																																												
	10%	10%	0603 \geq 0.68 μ F; 0805 \geq 2.2 μ F; 1206 \geq 4.7 μ F; 1210 \geq 22 μ F																																																																																												
16V	3.5%	5%	0402 \geq 0.33 μ F; 0603 \geq 0.33 μ F; 0805 \geq 2.2 μ F; 1206 \geq 2.2 μ F; 1210 \geq 22 μ F																																																																																												
	10%	10%	0201 \geq 0.1 μ F; 0402 \geq 1 μ F																																																																																												
10V	5%	10%	0603 \geq 10 μ F; 0805 \geq 4.7 μ F; 1206 \geq 47 μ F; 1210 \geq 100 μ F;																																																																																												
	15%	15%	0402 \geq 2.2 μ F																																																																																												
6.3V	10%	10%	0402 \geq 0.47 μ F																																																																																												
	20%	20%	---																																																																																												
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																																																													
\geq 50V	5%	7%	0603 \geq 0.1 μ F; 0805 \geq 0.47 μ F; 1206 \geq 4.7 μ F																																																																																												
35V	7%	---	---																																																																																												
25V	5%	7%	0402 \geq 0.047 μ F; 0603 \geq 0.1 μ F; 0805 \geq 0.33 μ F; 1206 \geq 1 μ F; 1210 \geq 4.7 μ F																																																																																												
	9%	9%	0402 \geq 0.068 μ F; 0603 \geq 0.47 μ F; 1206 \geq 4.7 μ F; 1210 \geq 22 μ F																																																																																												
16V (C<1.0 μ F)	7%	9%	0402 \geq 0.068 μ F; 0603 \geq 0.68 μ F																																																																																												
	12.5%	12.5%	0402 \geq 0.22 μ F																																																																																												
16V (C \geq 1.0 μ F)	9%	12.5%	0603 \geq 2.2 μ F; 0805 \geq 3.3 μ F; 1206 \geq 10 μ F; 1210 \geq 22 μ F; 1812 \geq 47 μ F																																																																																												
10V	12.5%	20%	0402 \geq 0.47 μ F																																																																																												
6.3V	20%	---	---																																																																																												
4.	Dielectric Strength	<ul style="list-style-type: none"> * To apply voltage (\leq100V) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA. 	<ul style="list-style-type: none"> * No evidence of damage or flash over during test. 																																																																																												
5.	Insulation Resistance	To apply rated voltage for max. 120 sec.	10G Ω or Rx C \geq 500 Ω -F whichever is smaller. Class II (X7R, X5R, Y5V)																																																																																												
			<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="4">10GΩ or Rx$C$$\geq$ 100Ω-F whichever is smaller.</td> </tr> <tr> <td>16V: 0402\geq 0.22μF</td> </tr> <tr> <td>10V: 0201\geq 47nF; 0402\geq 0.47μF; 0603\geq 0.47μF ; 0805\geq 2.2μF; 1206\geq 4.7μF; 1210\geq 47μF</td> </tr> <tr> <td>6.3V</td> </tr> </tbody> </table>	Rated voltage	Insulation Resistance	100V: X7R	10G Ω or Rx C \geq 100 Ω -F whichever is smaller.	16V: 0402 \geq 0.22 μ F	10V: 0201 \geq 47nF; 0402 \geq 0.47 μ F; 0603 \geq 0.47 μ F ; 0805 \geq 2.2 μ F; 1206 \geq 4.7 μ F; 1210 \geq 47 μ F	6.3V																																																																																					
Rated voltage	Insulation Resistance																																																																																														
100V: X7R	10G Ω or Rx C \geq 100 Ω -F whichever is smaller.																																																																																														
16V: 0402 \geq 0.22 μ F																																																																																															
10V: 0201 \geq 47nF; 0402 \geq 0.47 μ F; 0603 \geq 0.47 μ F ; 0805 \geq 2.2 μ F; 1206 \geq 4.7 μ F; 1210 \geq 47 μ F																																																																																															
6.3V																																																																																															
6.	Temperature Coefficient	With no electrical load.	<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>T.C.</th> <th>Operating Temp</th> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>NPO</td> <td>-55~125°C at 25°C</td> <td>NPO</td> <td>Within \pm30ppm/$^{\circ}$C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> <td>X7R</td> <td>Within \pm15%</td> </tr> <tr> <td>X5R</td> <td>-55~ 85°C at 25°C</td> <td>X5R</td> <td>Within \pm15%</td> </tr> <tr> <td>Y5V</td> <td>-25~ 85°C at 20°C</td> <td>Y5V</td> <td>Within +30%/-80%</td> </tr> </tbody> </table>	T.C.	Operating Temp	T.C.	Capacitance Change	NPO	-55~125°C at 25°C	NPO	Within \pm 30ppm/ $^{\circ}$ C	X7R	-55~125°C at 25°C	X7R	Within \pm 15%	X5R	-55~ 85°C at 25°C	X5R	Within \pm 15%	Y5V	-25~ 85°C at 20°C	Y5V	Within +30%/-80%																																																																								
T.C.	Operating Temp	T.C.	Capacitance Change																																																																																												
NPO	-55~125°C at 25°C	NPO	Within \pm 30ppm/ $^{\circ}$ C																																																																																												
X7R	-55~125°C at 25°C	X7R	Within \pm 15%																																																																																												
X5R	-55~ 85°C at 25°C	X5R	Within \pm 15%																																																																																												
Y5V	-25~ 85°C at 20°C	Y5V	Within +30%/-80%																																																																																												
7.	Adhesive Strength of Termination	<ul style="list-style-type: none"> * Pressurizing force : 5N (\leq0603) and 10N ($>$0603) * Test time: 10\pm1 sec. 	<ul style="list-style-type: none"> * No remarkable damage or removal of the terminations. 																																																																																												

No.	Item	Test Condition	Requirements															
8.	Vibration Resistance	<ul style="list-style-type: none"> * Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change and Q/D.F.: To meet initial spec. 															
9.	Solderability	<ul style="list-style-type: none"> * Solder temperature: 235±5°C * Dipping time: 2±0.5 sec. 	95% min. coverage of all metallized area.															
10.	Bending Test	<ul style="list-style-type: none"> * The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change : NP0: within ±5% or 0.5pF whichever is larger X7R, X5R: within ±12.5% Y5V: within ±30% (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.) 															
11.	Resistance to Soldering Heat	<ul style="list-style-type: none"> * Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge. 															
12.	Temperature Cycle	<ul style="list-style-type: none"> * Conduct the five cycles according to the temperatures and time. <table border="1" style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> <ul style="list-style-type: none"> * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II). 	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	<ul style="list-style-type: none"> No remarkable damage. Cap change : NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements.
Step	Temp. (°C)	Time (min.)																
1	Min. operating temp. +0/-3	30±3																
2	Room temp.	2~3																
3	Max. operating temp. +3/-0	30±3																
4	Room temp.	2~3																



No.	Item	Test Condition			Requirements							
13.	Humidity (Damp Heat) Steady State	<ul style="list-style-type: none"> * Test temp.: $40 \pm 2^\circ\text{C}$ * Humidity: 90~95% RH * Test time: $500 \pm 24/-\text{hrs}$. * Measurement to be made after keeping at room temp. for 24 ± 2 hrs. (Class I) or 48 ± 4 hrs. (Class II). 			<ul style="list-style-type: none"> * No remarkable damage. * Cap change: NP0: within $\pm 5\%$ or $0.5\mu\text{F}$ whichever is larger X7R, X5R: $\geq 10\text{V}$, within $\pm 12.5\%$; 6.3V, within $\pm 25\%$ Y5V: $\geq 10\text{V}$, within $\pm 30\%$; 6.3V, within $+30/-40\%$ * Q/D.F. value: NP0: More than 30pF $Q \geq 350$, $10\text{pF} \leq C \leq 30\text{pF}$, $Q \geq 275 \pm 2.5\text{C}$ Less than 10pF $Q \geq 200 \pm 10\text{C}$ 							
		X7R, X5R:	Rated vol.	D.F. \leq	Exception of D.F. \leq							
			$\geq 50\text{V}$	3%	6%	$0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$						
			25V	5%	10%	$0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$						
					14%	$0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$						
					15%	$0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$						
			16V	5%	10%	$0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$						
					15%	$0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$						
			10V	7.5%	15%	$0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$						
					20%	$0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$						
			6.3V	15%	30%	$0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$						
		Y5V:	Rated vol.	D.F. \leq	Exception of D.F. \leq							
			$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$						
			35V	10%	---	---						
			25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$						
					15%	$0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$						
			16V (C<1.0μF)	10%	12.5%	$0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$						
					20%	$0402 \geq 0.22\mu\text{F}$						
			16V (C≥ 1.0μF)	12.5%	20%	$0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$						
			10V	20%	30%	$0402 \geq 0.47\mu\text{F}$						
			6.3V	30%	---	---						
		*I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller.			Class II (X7R, X5R, Y5V)							
		Rated voltage			Insulation Resistance							
		100V: X7R			1 $\text{G}\Omega$ or $R \times C \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.							
		16V: 0402≥0.22μF										
		10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; ; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF										
		6.3V										

No	Item	Test Condition	Requirements																																																																																							
14	Humidity (Damp Heat) Load	<ul style="list-style-type: none"> * Test temp.: $40 \pm 2^\circ\text{C}$ * Humidity: 90~95%RH * Test time: $500+24/-0$ hrs. * To apply voltage : rated voltage. * Measurement to be made after keeping at room temp. for 24 ± 2 hrs. (Class I) or 48 ± 4 hrs. (Class II). 	<p>* No remarkable damage. Cap change: NP0: $\pm 7.5\%$ or $0.75\mu\text{F}$ whichever is larger. X7R, X5R: $\geq 10\text{V}$, within $\pm 12.5\%$; 6.3V, within $\pm 25\%$ Y5V: $\geq 10\text{V}$, within $\pm 30\%$; 6.3V, within $+30/-40\%$ Q/D.F. value: NP0: $C \geq 30\mu\text{F}, Q \geq 200; C < 30\mu\text{F}, Q \geq 100 + 10/3\text{C}$ X7R, X5R:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th>Exception of D.F.≤</th> </tr> </thead> <tbody> <tr> <td rowspan="4">$\geq 50\text{V}$</td> <td rowspan="4">3%</td> <td>0603$\geq 0.047\mu\text{F}$; 0805$\geq 0.18\mu\text{F}$; 1206$\geq 0.47\mu\text{F}$</td> </tr> <tr> <td>0805$\geq 1\mu\text{F}$; 1210$\geq 10\mu\text{F}$</td> </tr> <tr> <td>0603$\geq 0.33\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>0402$\geq 0.10\mu\text{F}$; 0603$\geq 0.47\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$; 1206$\geq 6.8\mu\text{F}$</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">5%</td> <td>0603$\geq 0.15\mu\text{F}$; 0805$\geq 0.68\mu\text{F}$; 1206$\geq 2.2\mu\text{F}$; 1210$\geq 4.7\mu\text{F}$,</td> </tr> <tr> <td>0402$\geq 0.033\mu\text{F}$; 0603$\geq 0.68\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$</td> </tr> <tr> <td>1206$\geq 4.7\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td> </tr> <tr> <td>0402$\geq 0.33\mu\text{F}$; 0603$\geq 0.33\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$</td> </tr> <tr> <td rowspan="4">16V</td> <td rowspan="4">5%</td> <td>10% 15%</td> <td>0402$\geq 0.33\mu\text{F}$; 0603$\geq 0.68\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$</td> </tr> <tr> <td>1206$\geq 2.2\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td> </tr> <tr> <td>0201$\geq 0.1\mu\text{F}$; 0402$\geq 1\mu\text{F}$</td> </tr> <tr> <td>0402$\geq 2.2\mu\text{F}$; 0603$\geq 10\mu\text{F}$; 0805$\geq 4.7\mu\text{F}$; 1206$\geq 47\mu\text{F}$; 1210$\geq 100\mu\text{F}$</td> </tr> <tr> <td rowspan="10">10V</td> <td rowspan="10">7.5%</td> <td>15% 20%</td> <td>0402$\geq 0.33\mu\text{F}$; 0603$\geq 0.68\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$</td> </tr> <tr> <td>1206$\geq 2.2\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td> </tr> <tr> <td>0201$\geq 0.1\mu\text{F}$; 0402$\geq 1\mu\text{F}$</td> </tr> <tr> <td>0402$\geq 2.2\mu\text{F}$; 0603$\geq 10\mu\text{F}$; 0805$\geq 4.7\mu\text{F}$; 1206$\geq 47\mu\text{F}$; 1210$\geq 100\mu\text{F}$</td> </tr> <tr> <td>6.3V</td> <td>15%</td> <td>30%</td> <td>0402$\geq 2.2\mu\text{F}$; 0603$\geq 10\mu\text{F}$; 0805$\geq 4.7\mu\text{F}$; 1206$\geq 47\mu\text{F}$; 1210$\geq 100\mu\text{F}$</td> </tr> <tr> <td colspan="4">Y5V:</td> </tr> <tr> <td rowspan="10">35V</td> <td rowspan="10">7.5%</td> <td>7.5% 10%</td> <td>0603$\geq 0.1\mu\text{F}$; 0805$\geq 0.47\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>10%</td> <td>---</td> <td>---</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">7.5%</td> <td>10% 15%</td> <td>0402$\geq 0.047\mu\text{F}$; 0603$\geq 0.1\mu\text{F}$; 0805$\geq 0.33\mu\text{F}$; 1206$\geq 1\mu\text{F}$; 1210$\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>15%</td> <td>0402$\geq 0.068\mu\text{F}$; 0603$\geq 0.47\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>10%</td> <td>12.5% 20%</td> <td>0402$\geq 0.068\mu\text{F}$; 0603$\geq 0.68\mu\text{F}$</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>12.5%</td> <td>20%</td> <td>0402$\geq 0.22\mu\text{F}$</td> </tr> <tr> <td>10V</td> <td>20%</td> <td>30%</td> <td>0603$\geq 2.2\mu\text{F}$; 0805$\geq 3.3\mu\text{F}$; 1206$\geq 10\mu\text{F}$; 1210$\geq 22\mu\text{F}$; 1812$\geq 47\mu\text{F}$</td> </tr> <tr> <td>6.3V</td> <td>30%</td> <td>---</td> <td>---</td> </tr> <tr> <td colspan="4">*I.R.: $\geq 10\text{V}$, $500\text{M}\Omega$ or $25\ \Omega\cdot\text{F}$ whichever is smaller. Class II (X7R, X5R, Y5V)</td> </tr> <tr> <td colspan="3">Rated voltage</td> <td>Insulation Resistance</td> </tr> <tr> <td colspan="3">100V: X7R</td> <td rowspan="4">500MΩ or $R \times C \geq 5\ \Omega\cdot\text{F}$ whichever is smaller.</td> </tr> <tr> <td colspan="3">16V: 0402$\geq 0.22\mu\text{F}$</td> </tr> <tr> <td colspan="3">10V: 0201$\geq 47\mu\text{F}$; 0402$\geq 0.47\mu\text{F}$; 0603$\geq 0.47\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$; 1210$\geq 47\mu\text{F}$</td> </tr> <tr> <td colspan="3">6.3V</td> </tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F.≤	$\geq 50\text{V}$	3%	0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$	0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$	0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$	25V	5%	0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$,	0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$	1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$	16V	5%	10% 15%	0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$	1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$	0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$	10V	7.5%	15% 20%	0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$	1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$	0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$	6.3V	15%	30%	0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$	Y5V:				35V	7.5%	7.5% 10%	0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$	10%	---	---	25V	7.5%	10% 15%	0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$	15%	0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	16V (C<1.0μF)	10%	12.5% 20%	0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$	16V (C≥1.0μF)	12.5%	20%	0402 $\geq 0.22\mu\text{F}$	10V	20%	30%	0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$	6.3V	30%	---	---	*I.R.: $\geq 10\text{V}$, $500\text{M}\Omega$ or $25\ \Omega\cdot\text{F}$ whichever is smaller. Class II (X7R, X5R, Y5V)				Rated voltage			Insulation Resistance	100V: X7R			500MΩ or $R \times C \geq 5\ \Omega\cdot\text{F}$ whichever is smaller.	16V: 0402 $\geq 0.22\mu\text{F}$			10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$			6.3V		
Rated vol.	D.F.≤	Exception of D.F.≤																																																																																								
$\geq 50\text{V}$	3%	0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$																																																																																								
		0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$																																																																																								
		0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$																																																																																								
		0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$																																																																																								
25V	5%	0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$,																																																																																								
		0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$																																																																																								
		1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																								
		0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$																																																																																								
16V	5%	10% 15%	0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$																																																																																							
		1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																								
		0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$																																																																																								
		0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$																																																																																								
10V	7.5%	15% 20%	0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$																																																																																							
		1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																								
		0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$																																																																																								
		0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$																																																																																								
		6.3V	15%	30%	0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$																																																																																					
		Y5V:																																																																																								
		35V	7.5%	7.5% 10%	0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$																																																																																					
				10%	---	---																																																																																				
				25V	7.5%	10% 15%	0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$																																																																																			
						15%	0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																			
16V (C<1.0μF)	10%					12.5% 20%	0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$																																																																																			
16V (C≥1.0μF)	12.5%					20%	0402 $\geq 0.22\mu\text{F}$																																																																																			
10V	20%			30%	0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$																																																																																					
6.3V	30%			---	---																																																																																					
*I.R.: $\geq 10\text{V}$, $500\text{M}\Omega$ or $25\ \Omega\cdot\text{F}$ whichever is smaller. Class II (X7R, X5R, Y5V)																																																																																										
Rated voltage				Insulation Resistance																																																																																						
100V: X7R			500MΩ or $R \times C \geq 5\ \Omega\cdot\text{F}$ whichever is smaller.																																																																																							
16V: 0402 $\geq 0.22\mu\text{F}$																																																																																										
10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$																																																																																										
6.3V																																																																																										


No	Item	Test Condition				Requirements																																																																																																																																
15.	High Temperature Load (Endurance)	* Test temp. : NP0, X7R/X7E: $125 \pm 3^\circ\text{C}$ X5R, Y5V: $85 \pm 3^\circ\text{C}$ * Test time: $1000+24/-0$ hrs. * To apply voltage: (1) 6.3V or $C \geq 10\mu\text{F}$ or TT series: 150% of rated voltage. (2) $10V \leq Ur < 500\text{V}$: 200% of rated voltage. (3) 500V : 150% of rated voltage. (4) $Ur \geq 630\text{V}$: 120% of rated voltage. (5) 100% of rated voltage for below range. <table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0201</td><td>X5R</td><td>6.3V,10V</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td>0402</td><td>X5R, Y5V</td><td>6.3V,10V</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R</td><td>6.3V,10V</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td></td><td>$TT \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R</td><td>6.3V</td><td>$C \geq 22\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td></td><td>$TT \geq 10\mu\text{F}$</td></tr> <tr> <td>1206</td><td>X5R</td><td>6.3V</td><td>$C \geq 47\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td></td><td>$TT \geq 22\mu\text{F}$</td></tr> </tbody> </table> (6) 150% of rated voltage for below range. <table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0402</td><td>X5R</td><td>10V,16V</td><td>$C \geq 0.22\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td>16V</td><td>$C \geq 0.47\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R</td><td>10V,16V</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td>16V</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R</td><td>10V</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td>16V</td><td>$C \geq 4.7\mu\text{F}$</td></tr> </tbody> </table>	Size	Dielectric	Rated voltage	Capacitance range	0201	X5R	6.3V,10V	$C \geq 0.1\mu\text{F}$	0402	X5R, Y5V	6.3V,10V	$C \geq 1.0\mu\text{F}$	0603	X5R	6.3V,10V	$C \geq 4.7\mu\text{F}$		Y5V		$TT \geq 2.2\mu\text{F}$	0805	X5R	6.3V	$C \geq 22\mu\text{F}$		Y5V		$TT \geq 10\mu\text{F}$	1206	X5R	6.3V	$C \geq 47\mu\text{F}$		Y5V		$TT \geq 22\mu\text{F}$	Size	Dielectric	Rated voltage	Capacitance range	0402	X5R	10V,16V	$C \geq 0.22\mu\text{F}$		Y5V	16V	$C \geq 0.47\mu\text{F}$	0603	X5R	10V,16V	$C \geq 1.0\mu\text{F}$		Y5V	16V	$C \geq 2.2\mu\text{F}$	0805	X5R	10V	$C \geq 4.7\mu\text{F}$		Y5V	16V	$C \geq 4.7\mu\text{F}$	* No remarkable damage. Cap change: NP0: $\pm 3.0\%$ or $\pm 0.3\text{pF}$ whichever is larger X7R, X5R: $\geq 10\text{V}$, within $\pm 12.5\%$; 6.3V , within $\pm 25\%$ Y5V: $\geq 10\text{V}$, within $\pm 30\%$; 6.3V , within $+30/-40\%$ Q/D.F. value: NP0: More than 30pF , $Q \geq 350$ $10\text{pF} \leq C < 30\text{pF}$, $Q \geq 275+2.5\text{C}$ Less than 10pF , $Q \geq 200+10\text{C}$ X7R, X5R: <table border="1"> <thead> <tr> <th>Rated vol.</th><th>D.F.≤</th><th>Exception of D.F.≤</th></tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td><td>3%</td><td>6% 0603$\geq 0.047\mu\text{F}$; 0805$\geq 0.18\mu\text{F}$; 1206$\geq 0.47\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>10% 0805$\geq 1\mu\text{F}$; 1210$\geq 10\mu\text{F}$</td></tr> <tr> <td>25V</td><td>5%</td><td>14% 0603$\geq 0.33\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% 0402$\geq 0.10\mu\text{F}$; 0603$\geq 0.47\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$; 1206$\geq 6.8\mu\text{F}$</td></tr> <tr> <td>16V</td><td>5%</td><td>10% 0603$\geq 0.15\mu\text{F}$; 0805$\geq 0.68\mu\text{F}$; 1206$\geq 2.2\mu\text{F}$; 1210$\geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% 0402$\geq 0.033\mu\text{F}$; 0603$\geq 0.68\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td></tr> <tr> <td>10V</td><td>7.5%</td><td>15% 0402$\geq 0.33\mu\text{F}$; 0603$\geq 0.33\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$; 1206$\geq 2.2\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>20% 0201$\geq 0.1\mu\text{F}$; 0402$\geq 1\mu\text{F}$</td></tr> <tr> <td>6.3V</td><td>15%</td><td>30% 0402$\geq 2.2\mu\text{F}$; 0603$\geq 10\mu\text{F}$; 0805$\geq 4.7\mu\text{F}$; 1206$\geq 47\mu\text{F}$; 1210$\geq 100\mu\text{F}$</td></tr> </tbody> </table> Y5V: <table border="1"> <thead> <tr> <th>Rated vol.</th><th>D.F.≤</th><th>Exception of D.F.≤</th></tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td><td>7.5%</td><td>10% 0603$\geq 0.1\mu\text{F}$; 0805$\geq 0.47\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$</td></tr> <tr> <td>35V</td><td>10%</td><td>---</td></tr> <tr> <td>25V</td><td>7.5%</td><td>10% 0402$\geq 0.047\mu\text{F}$; 0603$\geq 0.1\mu\text{F}$; 0805$\geq 0.33\mu\text{F}$; 1206$\geq 1\mu\text{F}$; 1210$\geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% 0402$\geq 0.068\mu\text{F}$; 0603$\geq 0.47\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$; 1210$\geq 22\mu\text{F}$</td></tr> <tr> <td>16V</td><td>10%</td><td>12.5% 0402$\geq 0.068\mu\text{F}$; 0603$\geq 0.68\mu\text{F}$</td></tr> <tr> <td>(C<1.0μF)</td><td></td><td>20% 0402$\geq 0.22\mu\text{F}$</td></tr> <tr> <td>16V</td><td>12.5%</td><td>20% 0603$\geq 2.2\mu\text{F}$; 0805$\geq 3.3\mu\text{F}$; 1206$\geq 10\mu\text{F}$; 1210$\geq 22\mu\text{F}$; 1812$\geq 47\mu\text{F}$</td></tr> <tr> <td>(C≥1.0μF)</td><td></td><td></td></tr> <tr> <td>10V</td><td>20%</td><td>30% 0402$\geq 0.47\mu\text{F}$</td></tr> <tr> <td>6.3V</td><td>30%</td><td>---</td></tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F.≤	$\geq 50\text{V}$	3%	6% 0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$			10% 0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	25V	5%	14% 0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$			15% 0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$	16V	5%	10% 0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$			15% 0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	10V	7.5%	15% 0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$			20% 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$	6.3V	15%	30% 0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$	Rated vol.	D.F.≤	Exception of D.F.≤	$\geq 50\text{V}$	7.5%	10% 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$	35V	10%	---	25V	7.5%	10% 0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$			15% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	16V	10%	12.5% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$	(C<1.0μF)		20% 0402 $\geq 0.22\mu\text{F}$	16V	12.5%	20% 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$	(C≥1.0μF)			10V	20%	30% 0402 $\geq 0.47\mu\text{F}$	6.3V	30%	---	* I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, Y5V)			
Size	Dielectric	Rated voltage	Capacitance range																																																																																																																																			
0201	X5R	6.3V,10V	$C \geq 0.1\mu\text{F}$																																																																																																																																			
0402	X5R, Y5V	6.3V,10V	$C \geq 1.0\mu\text{F}$																																																																																																																																			
0603	X5R	6.3V,10V	$C \geq 4.7\mu\text{F}$																																																																																																																																			
	Y5V		$TT \geq 2.2\mu\text{F}$																																																																																																																																			
0805	X5R	6.3V	$C \geq 22\mu\text{F}$																																																																																																																																			
	Y5V		$TT \geq 10\mu\text{F}$																																																																																																																																			
1206	X5R	6.3V	$C \geq 47\mu\text{F}$																																																																																																																																			
	Y5V		$TT \geq 22\mu\text{F}$																																																																																																																																			
Size	Dielectric	Rated voltage	Capacitance range																																																																																																																																			
0402	X5R	10V,16V	$C \geq 0.22\mu\text{F}$																																																																																																																																			
	Y5V	16V	$C \geq 0.47\mu\text{F}$																																																																																																																																			
0603	X5R	10V,16V	$C \geq 1.0\mu\text{F}$																																																																																																																																			
	Y5V	16V	$C \geq 2.2\mu\text{F}$																																																																																																																																			
0805	X5R	10V	$C \geq 4.7\mu\text{F}$																																																																																																																																			
	Y5V	16V	$C \geq 4.7\mu\text{F}$																																																																																																																																			
Rated vol.	D.F.≤	Exception of D.F.≤																																																																																																																																				
$\geq 50\text{V}$	3%	6% 0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$																																																																																																																																				
		10% 0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$																																																																																																																																				
25V	5%	14% 0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$																																																																																																																																				
		15% 0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$																																																																																																																																				
16V	5%	10% 0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$																																																																																																																																				
		15% 0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																																																																				
10V	7.5%	15% 0402 $\geq 0.33\mu\text{F}$; 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																																																																				
		20% 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$																																																																																																																																				
6.3V	15%	30% 0402 $\geq 2.2\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$																																																																																																																																				
Rated vol.	D.F.≤	Exception of D.F.≤																																																																																																																																				
$\geq 50\text{V}$	7.5%	10% 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$																																																																																																																																				
35V	10%	---																																																																																																																																				
25V	7.5%	10% 0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$																																																																																																																																				
		15% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																																																																																																				
16V	10%	12.5% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$																																																																																																																																				
(C<1.0μF)		20% 0402 $\geq 0.22\mu\text{F}$																																																																																																																																				
16V	12.5%	20% 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$																																																																																																																																				
(C≥1.0μF)																																																																																																																																						
10V	20%	30% 0402 $\geq 0.47\mu\text{F}$																																																																																																																																				
6.3V	30%	---																																																																																																																																				
		<table border="1"> <thead> <tr> <th>Rated voltage</th><th>Insulation Resistance</th></tr> </thead> <tbody> <tr> <td>100V: X7R</td><td rowspan="4">$1\text{G}\Omega$ or $RxC \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.</td></tr> <tr> <td>16V: 0402$\geq 0.22\mu\text{F}$</td></tr> <tr> <td>10V: 0201$\geq 47\mu\text{F}$; 0402$\geq 0.47\mu\text{F}$; 0603$\geq 0.47\mu\text{F}$; 0805$\geq 2.2\mu\text{F}$; 1206$\geq 4.7\mu\text{F}$; 1210$\geq 47\mu\text{F}$</td></tr> <tr> <td>6.3V</td></tr> </tbody> </table>				Rated voltage	Insulation Resistance	100V: X7R	$1\text{G}\Omega$ or $RxC \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.	16V: 0402 $\geq 0.22\mu\text{F}$	10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	6.3V																																																																																																																										
Rated voltage	Insulation Resistance																																																																																																																																					
100V: X7R	$1\text{G}\Omega$ or $RxC \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.																																																																																																																																					
16V: 0402 $\geq 0.22\mu\text{F}$																																																																																																																																						
10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$																																																																																																																																						
6.3V																																																																																																																																						

APPENDIXES

□ Tape & reel dimensions




Size	0402	0603	0805			1206			1210			1812	
	N	S, X	A	B	C, D, I	B	C, J, D	G, P	C, D	G, K	M	D, K	M
A₀	0.62±0.05	1.02±0.05	1.50±0.10	1.50±0.10	<1.57	2.00±0.10	<1.85	<1.95	<2.97	<2.97	<2.97	<3.81	<3.81
B₀	1.12±0.05	1.80±0.05	2.30±0.10	2.30±0.10	<2.40	3.50±0.10	<3.46	<3.67	<3.73	<3.73	<3.73	<5.30	<5.30
T	0.60±0.05	0.95±0.05	0.75±0.05	0.95±0.05	0.23±0.05	0.95±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.25±0.05	0.25±0.05
K₀	-	-	-	-	<2.50	-	<2.50	<2.50	<2.50	<2.50	<3.00	<2.50	<3.00
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	12.0±0.20	12.0±0.20
P₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP₀	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10
P₁	2.00±0.05	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	8.00±0.10	8.00±0.10
P₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D₀	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05
D₁	-	-	-	-	1.00±0.10	-	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.50±0.10	1.50±0.10
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	5.50±0.05	5.50±0.05



Size	0402, 0603, 0805, 1206, 1210			1812	
	Reel size	7"	10"	13"	7"
C	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2
W₁	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	12.4+2.0/-0
A	178.0±0.10	250.0±1.0	330.0±1.0	330.0±1.0	178.0±0.10
N	60.0+1.0/-0	100.0±1.0	100±1.0	100±1.0	60.0+1.0/-0

□ Description of customer label



- a. Customer name
- b. WTC order series and item number
- c. Customer P/O
- d. Customer P/N
- e. Description of product
- f. Quantity
- g. Bar code including quantity & WTC P/N or customer
- h. WTC P/N
- i. Shipping date
- j. Order bar code including series and item numbers
- k. Serial number of label

□ Constructions

No.	Name	X7R, X5R, Y5V
①	Ceramic material	BaTiO ₃ based
②	Inner electrode	Ni
③	Inner layer	Cu
④	Middle layer	Ni
⑤	Outer layer	Sn (Matt)




Fig. 9 The construction of MLCC

□ Storage and handling conditions

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70% related humidity conditions.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

Cautions:

- a. Don't store products in a corrosive environment such as sulfide, chloride gas, or acid. It may cause oxidization of electrode, which easily be resulted in poor soldering.
- b. To store products on the shelf and avoid exposure to moisture.
- c. Don't expose products to excessive shock, vibration, direct sunlight and so on.

□ Recommended soldering conditions

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N₂ within oven are recommended.




Fig. 10 Recommended IR reflow soldering profile for SMT process with SnAgCu series solder paste.




Fig. 11 Recommended wave soldering profile for SMT process with SnAgCu series solder.